



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> C07F 7/00, 7/28, C08F 10/00 C08F 4/642	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 91/04257</b>  <b>(43) International Publication Date:</b> 4 April 1991 (04.04.91)
<b>(21) International Application Number:</b> PCT/US90/05208 <b>(22) International Filing Date:</b> 13 September 1990 (13.09.90) <b>(30) Priority data:</b> 406,945                      13 September 1989 (13.09.89)    US 533,245                      4 June 1990 (04.06.90)        US <b>(60) Parent Applications or Grants</b> <b>(63) Related by Continuation</b> US                                      406,945 (CIP) Filed on                              13 September 1989 (13.09.89) US                                      533,245 (CIP) Filed on                              4 June 1990 (04.06.90) <b>(71) Applicant (for all designated States except US):</b> EXXON CHEMICAL PATENTS INC. [US/US]; 1900 East Linden Avenue, Linden, NJ 07036-0710 (US).		<b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only) :</b> CANICH, Jo, Ann [US/ US]; 900 Henderson Avenue, #808, Houston, TX 77058 (US).  <b>(74) Agents:</b> KURTZMAN, Myron, B. et al.; Exxon Chemical Company, P.O. Box 5200, Baytown, TX 77522-5200 (US).  <b>(81) Designated States:</b> AT (European patent), AU, BE (Euro- pean patent), BR, CA, CH (European patent), DE (Eu- ropean patent)*, DK (European patent), ES (European patent), FI, FR (European patent), GB (European pa- tent), IT (European patent), JP, KR, LU (European pa- tent), NL (European patent), NO, SE (European patent), SU, US.  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
<b>(54) Title:</b> MONOCYCLOPENTADIENYL TRANSITION METAL OLEFIN POLYMERIZATION CATALYSTS  <b>(57) Abstract</b>  The invention is a catalyst system including a Group IV B transition metal component and an alumoxane component which may be employed to polymerize olefins to produce a high molecular weight polymer.		

### DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

#### FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MC	Monaco
AU	Australia	FI	Finland	MG	Madagascar
BB	Barbados	FR	France	ML	Mali
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GR	Greece	NL	Netherlands
BJ	Benin	HU	Hungary	NO	Norway
BR	Brazil	IT	Italy	PL	Poland
CA	Canada	JP	Japan	RO	Romania
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	LI	Licchtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
DE	Germany	LU	Luxembourg	TD	Chad
DK	Denmark			TG	Togo
				US	United States of America

## MONOCYCLOPENTADIENYL TRANSITION METAL OLEFIN POLYMERIZATION CATALYSTS

SPECIFICATION

This application is a Continuation-in-Part of United States Patent Application Serial No. 533,245 filed June 4, 1990 which in turn is a continuation-in-part of United States Patent Application Serial No. 406,945 filed September 13, 1989.

FIELD OF THE INVENTION

This invention relates to certain monocyclopentadienyl metal compounds of a Group IV B transition metal of the Periodic Table of Elements, to a catalyst system comprising a monocyclopentadienyl Group IV B transition metal compound and an alumoxane, and to a process using such catalyst system for the production of polyolefins, particularly polyethylene, polypropylene and  $\alpha$ -olefin copolymers of ethylene and propylene having a high molecular weight. The catalyst system is highly active at low ratios of aluminum to the Group IV B transition metal, hence catalyzes the production of a polyolefin product containing low levels of catalyst metal residue. Titanium species of the catalyst are stable at high pressures in unsupported form, unlike their bis-cyclopentadienyl titanium compound counterparts, and exhibit the ability to catalyze the incorporation of higher  $\alpha$ -olefin comonomer contents for production of higher molecular weight  $\alpha$ -olefin copolymers than analogous zirconium and hafnium species of a monocyclopentadienyl transition metal compound.

BACKGROUND OF THE INVENTION

As is well known, various processes and catalysts exist for the homopolymerization or copolymerization of olefins. For many applications it is of primary importance for a polyolefin to have a high weight average molecular weight while having a relatively narrow molecular weight distribution. A high weight average molecular weight, when accompanied by a narrow

- 2 -

molecular weight distribution, provides a polyolefin or an ethylene- $\alpha$ -olefin copolymer with high strength properties.

5        Traditional Ziegler-Natta catalysts system -- a transition metal compound cocatalyzed by an aluminum alkyl -- are capable of producing polyolefins having a high molecular weight but a broad molecular weight distribution.

10        More recently a catalyst system has been developed wherein the transition metal compound has two or more cyclopentadienyl ring ligands -- such transition metal compound being referred to as a metallocene -- which catalyzes the production of olefin monomers to polyolefins. Accordingly, 15 metallocene compounds of a Group IV B metal, particularly, titanocenes and zirconocenes, have been utilized as the transition metal component in such "metallocene" containing catalyst system for the production of polyolefins and ethylene- $\alpha$ -olefin 20 copolymers. When such metallocenes are cocatalyzed with an aluminum alkyl -- as is the case with a traditional type Ziegler-Natta catalyst system -- the catalytic activity of such metallocene catalyst system is generally too low to be of any commercial interest.

25        It has since become known that such metallocenes may be cocatalyzed with an alumoxane -- rather than an aluminum alkyl -- to provide a metallocene catalyst system of high activity for the production of polyolefins.

30        The zirconium metallocene species, as cocatalyzed or activated with an alumoxane, are commonly more active than their hafnium or titanium analogous for the polymerization of ethylene alone or together with an  $\alpha$ -olefin comonomer. When employed in a non- 35 supported form -- i.e., as a homogeneous or soluble catalyst system -- to obtain a satisfactory rate of productivity even with the most active zirconium

- 3 -

species of metallocene typically requires the use of a quantity of alumoxane activator sufficient to provide an aluminum atom to transition metal atom ratio (Al:TM) of at least greater than 1000:1; often  
5 greater than 5000:1, and frequently on the order of 10,000:1. Such quantities of alumoxane impart to a polymer produced with such catalyst system an undesirable content of catalyst metal residue, i.e., an undesirable "ash" content (the nonvolatile metal  
10 content). In high pressure polymerization procedures using soluble catalyst systems wherein the reactor pressure exceeds about 500 bar only the zirconium or hafnium species of metallocenes may be used. Titanium species of metallocenes are generally unstable at such  
15 high pressures unless deposited upon a catalyst support. A wide variety of Group IV B transition metal compounds have been named as possible candidates for an alumoxane cocatalyzed catalyst system. Although bis(cyclopentadienyl) Group IV B transition  
20 metal compounds have been the most preferred and heavily investigated for use in alumoxane activated catalyst systems for polyolefin production, suggestions have appeared that mono and tris(cyclopentadienyl) transition metal compounds may  
25 also be useful. See, for example U.S. Patent Nos. 4,522,982; 4,530,914 and 4,701,431. Such mono(cyclopentadienyl) transition metal compounds as have heretofore been suggested as candidates for an alumoxane activated catalyst system are  
30 mono(cyclopenta-dienyl) transition metal trihalides and trialkyls.

More recently, International Publication No. WO 87/03887 describes the use of a composition comprising a transition metal coordinated to at least one  
35 cyclopentadienyl and at least one heteroatom ligand as a transition metal component for use in an alumoxane activated catalyst system for  $\alpha$ -olefin polymerization.

- 4 -

The composition is broadly defined as a transition metal, preferably of Group IV B of the Periodic Table, which is coordinated with at least one cyclopentadienyl ligand and one to three heteroatom ligands, the balance of the transition metal coordination requirement being satisfied with cyclopentadienyl or hydrocarbyl ligands. Catalyst systems described by this reference are illustrated solely with reference to transition metal compounds which are metallocenes, i.e., bis(cyclopentadienyl) Group IV B transition metal compounds.

Even more recently, at the Third Chemical Congress of North American held in Toronto, Canada in June 1988, John Bercaw reported upon efforts to use a compound of a Group III B transition metal coordinated to a single cyclopentadienyl heteroatom bridged ligand as a catalyst system for the polymerization of olefins. Although some catalytic activity was observed under the conditions employed, the degree of activity and the properties observed in the resulting polymer product were discouraging of a belief that such monocyclopentadienyl transition metal compound could be usefully employed for commercial polymerization processes.

A need still exists for discovering catalyst systems that permit the production of higher molecular weight polyolefins and desirably with a narrow molecular weight distribution. It is further desirable that a catalyst be discovered which, within reasonable ranges of ethylene to  $\alpha$ -olefin monomer ratios, will catalyze the incorporation of higher contents of  $\alpha$ -olefin comonomers in the production of ethylene- $\alpha$ -olefins copolymers.


#### SUMMARY OF THE INVENTION

The catalyst system of this invention comprises a transition metal component from Group IV B of the Periodic Table of the Elements (CRC Handbook of

- 5 -

Chemistry and Physics, 68th ed. 1987-1988) and an alumoxane component which may be employed in solution, slurry or bulk phase polymerization procedure to produce a polyolefin of high weight average molecular weight and relatively narrow molecular weight distribution.

The "Group IV B transition metal component" of the catalyst system is represented by the formula:



wherein: M is Zr, Hf or Ti in its highest formal oxidation state (+4,  $d^0$  complex);

$(\text{C}_5\text{H}_{5-y-x}\text{R}_x)$  is a cyclopentadienyl ring which is substituted with from zero to five substituent groups R, "x" is 0, 1, 2, 3, 4 or 5 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from a group consisting of  $\text{C}_1\text{-C}_{20}$  hydrocarbyl radicals, substituted  $\text{C}_1\text{-C}_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, and alkoxy radical or any other radical containing a Lewis acidic or basic functionality,  $\text{C}_1\text{-C}_{20}$  hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements; halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkylborido radicals or any other radical containing Lewis acidic or basic functionality; or  $(\text{C}_5\text{H}_{5-y-x}\text{R}_x)$  is a cyclopentadienyl

- 6 -

ring in which at least two adjacent R-groups are joined forming a  $C_4-C_{20}$  ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl,

(JR' $_{z-1-y}$ ) is a heteroatom ligand in which J is an element with a coordination number of three from Group V A or an element with a coordination number of two from Group VI A of the Periodic Table of Elements, preferably nitrogen, phosphorus, oxygen or sulfur, and each R' is, independently a radical selected from a group consisting of  $C_1-C_{20}$  hydrocarbyl radicals, substituted  $C_1-C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms are replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality, and "z" is the coordination number of the element J;

each Q may be independently any univalent anionic ligand such as a halide, hydride, or substituted or unsubstituted  $C_1-C_{20}$  hydrocarbyl, alkoxide, aryloxy, amide, arylamide, phosphide or arylphosphide, provided that where any Q is a hydrocarbyl such Q is different from  $(C_5H_5-y-xR_x)$ , or both Q together may be an alkylidene or a cyclometallated hydrocarbyl or any other divalent anionic chelating ligand;


"y" is 0 or 1 when w is greater than 0; y is 1 when w is 0; when "y" is 1, T is a covalent bridging group containing a Group IV A or V A element such as, but not limited to, a dialkyl, alkylaryl or diaryl silicon or germanium radical, alkyl or aryl phosphine or amine radical, or a hydrocarbyl radical such as methylene, ethylene and the like;

L is a neutral Lewis base such as diethylether, tetraethylammonium chloride, tetrahydrofuran, dimethylaniline, aniline, trimethylphosphine, n-butylamine, and the like; and "w" is a number from 0



- 7 -

to 3. L can also be a second transition metal compound of the same type such that the two metal centers M and M' are bridged by Q and Q', wherein M' has the same meaning as M and Q' has the same meaning as Q. Such dimeric compounds are represented by the formula:



The alumoxane component of the catalyst may be represented by the formulas: (R<sup>3</sup>-Al-O)<sub>m</sub>; R<sup>4</sup>(R<sup>5</sup>-Al-O)<sub>m</sub><sup>-</sup> AlR<sup>6</sup> or mixtures thereof, wherein R<sup>3</sup>-R<sup>6</sup> are, independently, a C<sub>1</sub>-C<sub>5</sub> alkyl group or halide and "m" is an integer ranging from 1 to about 50 and preferably is from about 13 to about 25.

Catalyst systems of the invention may be prepared by placing the "Group IV B transition metal component" and the alumoxane component in common solution in a normally liquid alkane or aromatic solvent, which solvent is preferably suitable for use as a polymerization diluent for the liquid phase polymerization of an olefin monomer. Those species of the Group IV B transition metal component wherein the metal is titanium have been found to impart beneficial properties to a catalyst system which are unexpected in view of what is known about the properties of bis(cyclopentadienyl) titanium compounds which are cocatalyzed by alumoxanes. Whereas titanocenes in their soluble form are generally unstable in the presence of aluminum alkyls, the

- 8 -

monocyclopentadienyl titanium metal components of this invention, particularly those wherein the heteroatom is nitrogen, generally exhibit greater stability in the presence of aluminum alkyls, higher catalyst activity rates and higher  $\alpha$ -olefin comonomer incorporation.

Further, the titanium species of the Group IV B transition metal component catalyst of this invention generally exhibit higher catalyst activities and the production of polymers of greater molecular weight and  $\alpha$ -olefin comonomer contents than catalyst systems prepared with the zirconium or hafnium species of the Group IV B transition metal component.


A typical polymerization process of the invention such as for the polymerization or copolymerization of ethylene comprises the steps of contacting ethylene or  $C_3$ - $C_{20}$   $\alpha$ -olefins alone, or with other unsaturated monomers including  $C_3$ - $C_{20}$   $\alpha$ -olefins,  $C_5$ - $C_{20}$  diolefins, and/or acetylenically unsaturated monomers either alone or in combination with other olefins and/or other unsaturated monomers, with a catalyst comprising, in a suitable polymerization diluent, the Group IV B transition metal component illustrated above; and a methylalumoxane in an amount to provide a molar aluminum to transition metal ratio of from about 1:1 to about 20,000:1 or more; and reacting such monomer in the presence of such catalyst system at a temperature of from about  $-100^\circ\text{C}$  to about  $300^\circ\text{C}$  for a time of from about 1 second to about 10 hours to produce a polyolefin having a weight average molecular weight of from about 1,000 or less to about 5,000,000 or more and a molecular weight distribution of from about 1.5 to about 15.0.

#### DESCRIPTION OF THE PREFERRED EMBODIMENT

##### Catalyst Component

The Group IV B transition metal component of the catalyst system is represented by the general formula:

- 9 -



wherein M is Zr, Hf or Ti in its highest formal oxidation state (+4,  $d^0$  complex);

( $C_5H_{5-y-x}R_x$ ) is a cyclopentadienyl ring which is substituted with from zero to five substituent groups R, "x" is 0, 1, 2, 3, 4 or 5 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from a group consisting of  $C_1$ - $C_{20}$  hydrocarbyl radicals, substituted  $C_1$ - $C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality,  $C_1$ - $C_{20}$  hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements; and halogen radicals amido radicals, phosphido radicals, alkoxy radicals, alkylborido radicals or any other radical containing Lewis acidic or basic functionality; or ( $C_5H_{5-y-x}R_x$ ) is a cyclopentadienyl ring in which two adjacent R-groups are joined forming  $C_4$ - $C_{20}$  ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl;

( $JR'_{z-1-y}$ ) is a heteroatom ligand in which J is an element with a coordination number of three from Group V A or an element with a coordination number of two from Group VI A of the Periodic Table of Elements, preferably nitrogen, phosphorus, oxygen or sulfur with nitrogen being preferred, and each  $R'$  is,

- 10 -


independently a radical selected from a group consisting of  $C_1-C_{20}$  hydrocarbyl radicals, substituted  $C_1-C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, and alkoxy radical or any other radical containing a Lewis acidic or basic functionality, and "z" is the coordination number of the element J;

each Q is, independently, any univalent anionic ligand such as a halide, hydride, or substituted or unsubstituted  $C_1-C_{20}$  hydrocarbyl, alkoxide, aryloxy, amide, arylamide, phosphide or arylphosphide, provided that where any Q is a hydrocarbyl such Q is different from  $(C_5H_5-y-xR_x)$ , or both Q together may be an alkylidene or a cyclometallated hydrocarbyl or any other divalent anionic chelating ligand;

"y" is 0 or 1 when w is greater than 0, and y is 1 when w equals 0; when "y" is 1, T is a covalent bridging group containing a Group IV A or V A element such as, but not limited to, a dialkyl, alkylaryl or diaryl silicon or germanium radical, alkyl or aryl phosphine or amine radical, or a hydrocarbyl radical such as methylene, ethylene and the like; and

L is a neutral Lewis base such as diethylether, tetrahydrofuran, dimethylaniline, aniline, trimethylphosphine, n-butylamine, and the like; and "w" is a number from 0 to 3; L can also be a second transition metal compound of the same type such that the two metal centers M and M' are bridged by Q and Q', wherein M' has the same meaning as M and Q' has the same meaning as Q. Such compounds are represented by the formula:

- 11 -



Examples of the T group which are suitable as a constituent group of the Group IV B transition metal component of the catalyst system are identified in column 1 of Table 1 under the heading "T".

- 5 Exemplary hydrocarbyl radicals for Q are methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl and the like, with methyl being preferred.
- 10 Exemplary halogen atoms for Q include chlorine, bromine, fluorine and iodine, with chlorine being preferred. Exemplary alkoxides and aryloxides for Q are methoxide, phenoxide and substituted phenoxides such as 4-methylphenoxide. Exemplary amides of Q are dimethylamide, diethylamide, methylethylamide, di-*t*-butylamide, diisopropylamide and the like.
- 15 Exemplary aryl amides are diphenylamide and any other substituted phenyl amides. Exemplary phosphides of Q are diphenylphosphide, dicyclohexylphosphide, diethylphosphide, dimethylphosphide and the like.
- 20 Exemplary alkyldiene radicals for both Q together are methylenidene, ethylenidene and propylenidene. Examples of the Q group which are suitable as a constituent group or element of the Group IV B transition metal component of the catalyst system are identified in column 4 of Table 1 under the heading "Q".
- 25

Suitable hydrocarbyl and substituted hydrocarbyl radicals, which may be substituted as an R group for at least one hydrogen atom in the cyclopentadienyl ring, will contain from 1 to about 20 carbon atoms and

- 12 -

include straight and branched alkyl radicals, cyclic hydrocarbon radicals, alkyl-substituted cyclic hydrocarbon radicals, aromatic radicals and alkyl-substituted aromatic radicals, amido-substituted hydrocarbon radicals, phosphido-substituted hydrocarbon radicals, alkoxy-substituted hydrocarbon radicals, and cyclopentadienyl rings containing one or more fused saturated or unsaturated rings. Suitable organometallic radicals, which may be substituted as an R group for at least one hydrogen atom in the cyclopentadienyl ring, include trimethylsilyl, triethylsilyl, ethyldimethylsilyl, methyldiethylsilyl, triphenylgermyl, trimethylgermyl and the like. Other suitable radicals that may be substituted for one or more hydrogen atom in the cyclopentadienyl ring include halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkyl boride radicals and the like. Examples of cyclopentadienyl ring groups ( $C_5H_{5-y-x}R_x$ ) which are suitable as a constituent group of the Group IV B transition metal component of the catalyst system are identified in Column 2 of Table 1 under the heading ( $C_5H_{5-y-x}R_x$ ).

Suitable hydrocarbyl and substituted hydrocarbyl radicals, which may be substituted as an R' group for at least one hydrogen atom in the heteroatom J ligand group, will contain from 1 to about 20 carbon atoms and include straight and branched alkyl radicals, cyclic hydrocarbon radicals, alkyl-substituted cyclic hydrocarbon radicals, aromatic radicals, alkyl-substituted aromatic radicals, halogen radicals, amido radicals, phosphido radicals and the like. Examples of heteroatom ligand groups ( $JR'_{z-1-y}$ ) which are suitable as a constituent group of the Group IV B transition metal component of the catalyst system are identified in column 3 of Table 1 under the heading ( $JR'_{z-1-y}$ ).

Table 1 depicts representative constituent moieties for the "Group IV B transition metal

- 13 -

component", the list is for illustrative purposes only and should not be construed to be limiting in any way. A number of final components may be formed by permuting all possible combinations of the constituent moieties with each other. Illustrative compounds are:

5 dimethylsilyltetramethylcyclopentadienyl-tert-butylamido zirconium dichloride, dimethylsilyltetramethylcyclopentadienyl-tert-butylamido hafnium dichloride, dimethylsilyl-tert-butylcyclopentadienyl-tert-butylamido zirconium dichloride, dimethylsilyl-tert-butylcyclopentadienyl-tert-butylamido hafnium dichloride, dimethylsilyltrimethylsilylcyclopentadienyl-tert-butylamido zirconium dichloride, dimethylsilyltetramethylcyclopentadienylphenylamido zirconium dichloride, dimethylsilyltetramethylcyclopentadienylphenylamido hafnium dichloride, methylphenylsilyltetramethylcyclopentadienyl-tert-butylamido zirconium dichloride, methylphenylsilyltetramethylcyclopentadienyl-tert-butylamido hafnium dichloride, methylphenylsilyltetramethylcyclopentadienyl-tert-butylamido hafnium dichloride, methylphenylsilyltetramethylcyclopentadienyl-p-n-butylphenylamido zirconium dichloride, dimethylsilyltetramethylcyclopentadienyl-p-n-butylphenylamido hafnium dichloride.

10  
15  
20  
25

As noted, titanium species of the Group IV B transition metal compound have generally been found to yield catalyst systems which in comparison to their zirconium or hafnium analogs, are of higher activity and  $\alpha$ -olefin comonomer incorporating ability. Illustrative, but not limiting of the titanium species which exhibit such superior properties are methylphenylsilyltetramethylcyclopentadienyl-tert-butylamido titanium dichloride, dimethylsilyltetramethylcyclopentadienyl-p-n-butylphenylamido titanium dichloride, dimethylsilyltetramethylcyclopentadienyl-p-methoxyphenylamido titanium dichloride, dimethylsilyl-

30  
35

- 14 -

$\text{tert-butylcyclopentadienyl-2,5-di-tert-butylphenylamido}$  titanium dichloride,  
 $\text{dimethylsilylindenyl-tert-butyl-amido}$  titanium  
 dichloride,  $\text{dimethylsilyltetra-}$   
 5  $\text{methylcyclopentadienylcyclohexylamido}$  titanium  
 dichloride,  $\text{dimethylsilylfluorenylcyclohexylamido}$   
 titanium dichloride,  $\text{dimethylsilyltetramethyl-}$   
 $\text{cyclopentadienylphenylamido}$  titanium dichloride,  
 10  $\text{dimethylsilyltetramethylcyclopentadienyl-tert-}$   
 $\text{butylamido}$  titanium dichloride,  
 $\text{dimethylsilyltetramethyl-}$   
 $\text{cyclopentadienylcyclododecylamidotitaniumdichloride,}$   
 and the like.

For illustrative purposes, the above compounds  
 15 and those permuted from Table 1 do not include the  
 neutral Lewis base ligand (L). The conditions under  
 which complexes containing neutral Lewis base ligands  
 such as ether or those which form dimeric compounds is  
 determined by the steric bulk of the ligands about the  
 20 metal center. For example, the  $\text{t-butyl}$  group in  
 $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{ZrCl}_2$  has greater steric  
 requirements than the phenyl group in  
 $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh})\text{ZrCl}_2 \cdot \text{Et}_2\text{O}$  thereby not permitting  
 ether coordination in the former compound. Similarly,  
 25 due to the decreased steric bulk of the  
 $\text{trimethylsilylcyclopentadienyl}$  group in  
 $[\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_3)(\text{N-t-Bu})\text{ZrCl}_2]_2$  versus that of the  
 $\text{tetramethylcyclopentadienyl}$  group in  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-}$   
 $\text{Bu})\text{ZrCl}_2$ , the former compound is dimeric and the  
 latter is not.





- 16 -

Generally the bridged species of the Group IV B transition metal compound ("y" = 1) are preferred. These compounds can be prepared by reacting a cyclopentadienyl lithium compound with a dihalo compound whereupon a lithium halide salt is liberated and a monohalo substituent becomes covalently bound to the cyclopentadienyl compound. The so substituted cyclopentadienyl reaction product is next reacted with a lithium salt of a phosphide, oxide, sulfide or amide (for the sake of illustrative purposes, a lithium amide) whereupon the halo element of the monohalo substituent group of the reaction product reacts to liberate a lithium halide salt and the amine moiety of the lithium amide salt becomes covalently bound to the substituent of the cyclopentadienyl reaction product. The resulting amine derivative of the cyclopentadienyl product is then reacted with an alkyl lithium reagent whereupon the labile hydrogen atoms, at the carbon atom of the cyclopentadienyl compound and at the nitrogen atom of the amine moiety covalently bound to the substituent group, react with the alkyl of the lithium alkyl reagent to liberate the alkane and produce a dilithium salt of the cyclopentadienyl compound. Thereafter the bridged species of the Group IV B transition metal compound is produced by reacting the dilithium salt cyclopentadienyl compound with a Group IV B transition metal preferably a Group IV B transition metal halide.

Unbridged species of the Group IV B transition metal compound can be prepared from the reaction of a

- 17 -

cyclopentadienyl lithium compound and a lithium salt of an amine with a Group IV B transition metal halide.


Suitable, but not limiting, Group IV B transition metal compounds which may be utilized in the catalyst system of this invention include those bridged species ("y" = 1) wherein the T group bridge is a dialkyl, diaryl or alkylaryl silane, or methylene or ethylene. Exemplary of the more preferred species of bridged Group IV B transition metal compounds are dimethylsilyl, methylphenylsilyl, diethylsilyl, ethylphenylsilyl, diphenylsilyl, ethylene or methylene bridged compounds. Most preferred of the bridged species are dimethylsilyl, diethylsilyl and methylphenylsilyl bridged compounds.

Suitable Group IV B transition metal compounds which are illustrative of the unbridged ("y" = 0) species which may be utilized in the catalyst systems of this invention are exemplified by pentamethylcyclopentadienyldi-t-butylphosphinodimethyl hafnium; pentamethylcyclopentadienyldi-t-butylphosphinomethylethylhafnium; cyclopentadienyl-2-methylbutoxide dimethyl titanium.

To illustrate members of the Group IV B transition metal component, select any combination of the species in Table 1. An example of a bridged species would be dimethylsilylcyclopentadienyl-t-butylamidodichloro zirconium; an example of an unbridged species would be cyclopentadienyldi-t-butylamidodichloro zirconium.

- 18 -

Generally, wherein it is desired to produce an  $\alpha$ -olefin copolymer which incorporates a high content of  $\alpha$ -olefin, the species of Group IV B transition metal compound preferred is one of titanium. The most preferred species of titanium metal compounds are represented by the formula:



wherein Q, L, R', R, "x" and "w" are as previously defined and R<sup>1</sup> and R<sup>2</sup> are each independently a C<sub>1</sub> to C<sub>20</sub> hydrocarbyl radicals, substituted C<sub>1</sub> to C<sub>20</sub> hydrocarbyl radicals wherein one or more hydrogen atom is replaced by a halogen atom; R<sup>1</sup> and R<sup>2</sup> may also be joined forming a C<sub>3</sub> to C<sub>20</sub> ring which incorporates the silicon bridge.

The alumoxane component of the catalyst system is an oligomeric compound which may be represented by the general formula (R<sup>3</sup>-Al-O)<sub>m</sub> which is a cyclic compound, or may be R<sup>4</sup>(R<sup>5</sup>-Al-O)<sub>m</sub>-AlR<sup>6</sup><sub>2</sub> which is a linear compound. An alumoxane is generally a mixture of both the linear and cyclic compounds. In the general alumoxane formula R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> are, independently a C<sub>1</sub>-C<sub>5</sub> alkyl radical, for example, methyl, ethyl, propyl, butyl or pentyl and "m" is an integer from 1

-19-

to about 50. Most preferably,  $R^3$ ,  $R^4$ ,  $R^5$  and  $R^6$  are each methyl and "m" is at least 4. When an alkyl aluminum halide is employed in the preparation of the alumoxane, one or more  $R^{3-6}$  groups may be halide.

5 As is now well known, alumoxanes can be prepared by various procedures. For example, a trialkyl aluminum may be reacted with water, in the form of a moist inert organic solvent; or the trialkyl aluminum may be contacted with a hydrated salt, such as  
10 hydrated copper sulfate suspended in an inert organic solvent, to yield an alumoxane. Generally, however prepared, the reaction of a trialkyl aluminum with a limited amount of water yields a mixture of both linear and cyclic species of alumoxane.

15 Suitable alumoxanes which may be utilized in the catalyst systems of this invention are those prepared by the hydrolysis of a trialkylaluminum; such as trimethylaluminum, triethylaluminum, tripropylaluminum; triisobutylaluminum, dimethylaluminumchloride,  
20 diisobutylaluminumchloride, diethylaluminumchloride, and the like. The most preferred alumoxane for use is methylalumoxane (MAO). Methylalumoxanes having an average degree of oligomerization of from about 4 to about 25 ("m" = 4 to 25), with a range of 13 to 25,  
25 are the most preferred.

#### Catalyst Systems

The catalyst systems employed in the method of the invention comprise a complex formed upon admixture of the Group IV B transition metal component with an  
30 alumoxane component. The catalyst system may be prepared by addition of the requisite Group IV B transition metal and alumoxane components to an inert solvent in which olefin polymerization can be carried out by a solution, slurry or bulk phase polymerization  
35 procedure.

The catalyst system may be conveniently prepared by placing the selected Group IV B transition metal

-20-

component and the selected alumoxane component, in any order of addition, in an alkane or aromatic hydrocarbon solvent -- preferably one which is also suitable for service as a polymerization diluent.

5 Where the hydrocarbon solvent utilized is also suitable for use as a polymerization diluent, the catalyst system may be prepared in situ in the polymerization reactor. Alternatively, the catalyst system may be separately prepared, in concentrated  
10 form, and added to the polymerization diluent in a reactor. Or, if desired, the components of the catalyst system may be prepared as separate solutions and added to the polymerization diluent in a reactor, in appropriate ratios, as is suitable for a continuous  
15 liquid phase polymerization reaction procedure. Alkane and aromatic hydrocarbons suitable as solvents for formation of the catalyst system and also as a polymerization diluent are exemplified by, but are not necessarily limited to, straight and branched chain  
20 hydrocarbons such as isobutane, butane, pentane, hexane, heptane, octane and the like, cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane and the like, and aromatic and alkyl-substituted  
25 aromatic compounds such as benzene, toluene, xylene and the like. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, propylene, 1-butene, 1-hexene and the like.

30 In accordance with this invention optimum results are generally obtained wherein the Group IV B transition metal compound is present in the polymerization diluent in a concentration of from about 0.0001 to about 1.0 millimoles/liter of diluent  
35 and the alumoxane component is present in an amount to provide a molar aluminum to transition metal ratio of from about 1:1 to about 20,000:1. Sufficient solvent

-21-

should be employed so as to provide adequate heat transfer away from the catalyst components during reaction and to permit good mixing.

5       The catalyst system ingredients -- that is, the Group IV B transition metal, the alumoxane, and polymerization diluent -- can be added to the reaction vessel rapidly or slowly. The temperature maintained during the contact of the catalyst components can vary widely, such as, for example, from 10       -10° to 300°C. Greater or lesser temperatures can also be employed. Preferably, during formation of the catalyst system, the reaction is maintained within a temperature of from about 25° to 100°C, most preferably about 25°C.

15       At all times, the individual catalyst system components, as well as the catalyst system once formed, are protected from oxygen and moisture. Therefore, the reactions to prepare the catalyst system are performed in an oxygen and moisture free atmosphere and, where the catalyst system is recovered 20       separately it is recovered in an oxygen and moisture free atmosphere. Preferably, therefore, the reactions are performed in the presence of an inert dry gas such as, for example, helium or nitrogen.

25       Polymerization Process

30       In a preferred embodiment of the process of this invention the catalyst system is utilized in the liquid phase (slurry, solution, suspension or bulk phase or combination thereof), high pressure fluid phase or gas phase polymerization of an olefin

-22-

monomer. These processes may be employed singularly or in series. The liquid phase process comprises the steps of contacting an olefin monomer with the catalyst system in a suitable polymerization diluent and reacting said monomer in the presence of said catalyst system for a time and at a temperature sufficient to produce a polyolefin of high molecular weight.

The monomer for such process may comprise ethylene alone, for the production of a homopolyethylene, or ethylene in combination with an  $\alpha$ -olefin having 3 to 20 carbon atoms for the production of an ethylene- $\alpha$ -olefin copolymer. Homopolymers of higher  $\alpha$ -olefin such as propylene, butene, styrene and copolymers thereof with ethylene and/or  $C_4$  or higher  $\alpha$ -olefins and diolefins can also be prepared. Conditions most preferred for the homo- or copolymerization of ethylene are those wherein ethylene is submitted to the reaction zone at pressures of from about 0.019 psia to about 50,000 psia and the reaction temperature is maintained at from about  $-100^\circ$  to about  $300^\circ C$ . The aluminum to transition metal molar ratio is preferably from about 1:1 to 18,000 to 1. A more preferable range would be 1:1 to 2000:1. The reaction time is preferably from about 10 seconds to about 1 hour. Without limiting in any way the scope of the invention, one means for carrying out the process of the present invention for production of a copolymer is as follows: in a stirred-tank reactor liquid  $\alpha$ -olefin monomer is



-23-

introduced, such as 1-butene. The catalyst system is introduced via nozzles in either the vapor or liquid phase. Feed ethylene gas is introduced either into the vapor phase of the reactor, or sparged into the liquid phase as is well known in the art. The reactor contains a liquid phase composed substantially of liquid  $\alpha$ -olefin comonomer, together with dissolved ethylene gas, and a vapor phase containing vapors of all monomers. The reactor temperature and pressure may be controlled via reflux of vaporizing  $\alpha$ -olefin monomer (autorefrigeration), as well as by cooling coils, jackets etc. The polymerization rate is controlled by the concentration of catalyst. The ethylene content of the polymer product is determined by the ratio of ethylene to  $\alpha$ -olefin comonomer in the reactor, which is controlled by manipulating the relative feed rates of these components to the reactor.

As before noted, a catalyst system wherein the Group IV B transition metal component is a titanium species has the ability to incorporate high contents of  $\alpha$ -olefin comonomers. Accordingly, the selection of the Group IV B transition metal component is another parameter which may be utilized as a control over the ethylene content of a copolymer within a reasonable ratio of ethylene to  $\alpha$ -olefin comonomer.

#### EXAMPLES

In the examples which illustrate the practice of the invention the analytical techniques described below were employed for the analysis of the resulting polyolefin products. Molecular weight determinations

-24-

for polyolefin products were made by Gel Permeation Chromatography (GPC) according to the following technique. Molecular weights and molecular weight distributions were measured using a Waters 150 gel permeation chromatograph equipped with a differential refractive index (DRI) detector and a Chromatix KMX-6 on-line light scattering photometer. The system was used at 135°C with 1,2,4-trichlorobenzene as the mobile phase. Shodex (Showa Denko America, Inc.) polystyrene gel columns 802, 803, 804 and 805 were used. This technique is discussed in "Liquid Chromatography of Polymers and Related Materials III", J. Cazes editor, Marcel Dekker, 1981, p. 207, which is incorporated herein by reference. No corrections for column spreading were employed; however, data on generally accepted standards, e.g. National Bureau of Standards Polyethylene 1484 and anionically produced hydrogenated polyisoprenes (an alternating ethylene-propylene copolymer) demonstrated that such corrections on Mw/Mn (= MWD) were less than 0.05 units. Mw/Mn was calculated from elution times. The numerical analyses were performed using the commercially available Beckman/CIS customized LALLS software in conjunction with the standard Gel Permeation package, run on a HP 1000 computer.

The following examples are intended to illustrate specific embodiments of the invention and are not intended to limit the scope of the invention.

All procedures were performed under an inert atmosphere of helium or nitrogen. Solvent choices are

-25-

often optional, for example, in most cases either pentane or 30-60 petroleum ether can be interchanged. The lithiated amides were prepared from the corresponding amines and either  $n$ -BuLi or MeLi. Published methods for preparing  $\text{LiHC}_5\text{Me}_4$  include C.M. Fendrick et al. Organometallics, 3, 819 (1984) and F.H. Köhler and K. H. Doll, Z. Naturforsch., 37b, 144 (1982). Other lithiated substituted cyclopentadienyl compounds are typically prepared from the corresponding cyclopentadienyl ligand and  $n$ -BuLi or MeLi, or by reaction of MeLi with the proper fulvene.  $\text{TiCl}_4$ ,  $\text{ZrCl}_4$  and  $\text{HfCl}_4$  were purchased from either Aldrich Chemical Company or Cerac.  $\text{TiCl}_4$  was typically used in its etherate form. The etherate,  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$ , can be prepared by gingerly adding  $\text{TiCl}_4$  to diethylether. Amines, silanes and lithium reagents were purchased from Aldrich Chemical Company or Petrarch Systems. Methylalumoxane was supplied by either Sherring or Ethyl Corp.

20

Examples A-L and AT-IT of Group IV B  
Transition Metal-Components

Example A

25

Compound A: Part 1.  $\text{Me}_4\text{HC}_5\text{Li}$  (10.0 g, 0.078 mol) was slowly added to a  $\text{Me}_2\text{SiCl}_2$  (11.5 ml, 0.095 mol, in 225 ml of tetrahydrofuran (thf) solution). The solution was stirred for 1 hour to assure complete reaction. The thf solvent was then removed via a vacuum to a cold trap held at  $-196^\circ\text{C}$ . Pentane was added to precipitate out the  $\text{LiCl}$ . The mixture was

30

-26-

filtered through Celite. The solvent was removed from the filtrate.  $\text{Me}_4\text{HC}_5\text{SiMe}_2\text{Cl}$  (15.34 g, 0.071 mol) was recovered as a pale yellow liquid.

5       Part 2.  $\text{Me}_4\text{HC}_5\text{SiMe}_2\text{Cl}$  (10.0 g, 0.047 mol) was slowly added to a suspension of  $\text{LiHN-t-Bu}$  (3.68 g, 0.047 mol, ~100 ml thf). The mixture was stirred overnight. The thf was then removed via a vacuum to a cold trap held at  $-196^\circ\text{C}$ . Petroleum ether (~100 ml) was added to precipitate out the  $\text{LiCl}$ . The mixture was  
10       filtered through Celite. The solvent was removed from the filtrate.  $\text{Me}_2\text{Si}(\text{Me}_4\text{HC}_5)(\text{HN-t-Bu})$  (11.14 g, 0.044 mol) was isolated as a pale yellow liquid.

15       Part 3.  $\text{Me}_2\text{Si}(\text{Me}_4\text{HC}_5)(\text{HN-t-Bu})$  (11.14 g, 0.044 mol) was diluted with ~100 ml  $\text{Et}_2\text{O}$ .  $\text{MeLi}$  (1.4 M, 64 ml, 0.090 mol) was slowly added. The mixture was allowed to stir for 1/2 hour after the final addition of  $\text{MeLi}$ . The ether was reduced in volume prior to filtering off the product. The product,  $[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})]\text{Li}_2$ , was washed with several  
20       small portions of ether, then vacuum dried.

25       Part 4.  $[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})]\text{Li}_2$  (3.0 g, 0.011 mol) was suspended in ~150 ml  $\text{Et}_2\text{O}$ .  $\text{ZrCl}_4$  (2.65 g, 0.011 mol) was slowly added and the resulting mixture was allowed to stir overnight. The ether was removed via a vacuum to a cold trap held at  $-196^\circ\text{C}$ . Pentane was added to precipitate out the  $\text{LiCl}$ . The mixture was filtered through Celite twice. The pentane was significantly reduced in volume and the pale yellow solid was filtered off and washed with solvent.  
30        $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{ZrCl}_2$  (1.07 g, 0.0026 mole) was

-27-

recovered. Additional  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N}-t\text{-Bu})\text{ZrCl}_2$  was recovered from the filtrate by repeating the recrystallization procedure. Total yield, 1.94 g, 0.0047 mol.

5

Example B

Compound B: The same procedure of Example A for preparing compound A was followed with the exception of the use of  $\text{HfCl}_4$  in place of  $\text{ZrCl}_4$  in Part 4. Thus, when  $[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N}-t\text{-Bu})]\text{Li}_2$  (2.13 g, 0.0081 mol) and  $\text{HfCl}_4$  (2.59 g, 0.0081 mol) were used,  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N}-t\text{-Bu})\text{HfCl}_2$  (0.98 g, 0.0020 mol) was produced.

10

Example C

Compound C: Part 1.  $\text{Me}_2\text{SiCl}_2$  (7.5 ml, 0.062 mol) was diluted with ~30 ml thf. A  $t\text{-BuH}_4\text{C}_5\text{Li}$  solution (7.29 g, 0.056 mol, ~100 ml thf) was slowly added, and the resulting mixture was allowed to stir overnight. The thf was removed via a vacuum to a trap held at  $-196^\circ\text{C}$ . Pentane was added to precipitate out the  $\text{LiCl}$ , and the mixture was filtered through Celite. The pentane was removed from the filtrate leaving behind a pale yellow liquid,  $t\text{-BuH}_4\text{C}_5\text{SiMe}_2\text{Cl}$  (10.4 g, 0.048 mol).

15

20

Part 2. To a thf solution of  $\text{LiHN}-t\text{-Bu}$  (3.83 g, 0.048 mol, ~125 ml),  $t\text{-BuH}_4\text{C}_5\text{SiMe}_2\text{Cl}$  (10.4 g, 0.048 mol) was added drop wise. The resulting solution was allowed to stir overnight. The thf was removed via a vacuum to a trap held at  $-196^\circ\text{C}$ . Pentane was added to precipitate out the  $\text{LiCl}$ , and the mixture was filtered through Celite. The pentane was removed from the

25

30

-28-

filtrate leaving behind a pale yellow liquid,  $\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_4\text{C}_5)(\text{NH-}\underline{\text{t}}\text{-Bu})$  (11.4 g, 0.045 mol).

5       Part 3.  $\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_4\text{C}_5)(\text{NH-}\underline{\text{t}}\text{-Bu})$  (11.4 g, 0.045 mol) was diluted with ~100 ml  $\text{Et}_2\text{O}$ .  $\text{MeLi}$  (1.4 M, 70 ml, 0.098 mol) was slowly added. The mixture was allowed to stir overnight. The ether was removed via a vacuum to a trap held at  $-196^\circ\text{C}$ , leaving behind a pale yellow solid,  $[\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_3\text{C}_5)(\text{N-}\underline{\text{t}}\text{-Bu})]\text{Li}_2$  (11.9 g, 0.045 mol).

10       Part 4.  $[\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_3\text{C}_5)(\text{N-}\underline{\text{t}}\text{-Bu})]\text{Li}_2$  (3.39 g 0.013 mol) was suspended in ~100 ml  $\text{Et}_2\text{O}$ .  $\text{ZrCl}_4$  (3.0 g, 0.013 mol) was slowly added. The mixture was allowed to stir overnight. The ether was removed and pentane was added to precipitate out the  $\text{LiCl}$ . The mixture was filtered through Celite. The pentane solution was reduced in  
15       volume, and the pale tan solid was filtered off and washed several times with small quantities of pentane. The product of empirical formula  $\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_3\text{C}_5)(\text{N-}\underline{\text{t}}\text{-Bu})\text{ZrCl}_2$  (2.43 g, 0.0059 mol) was isolated.

20

#### Example D

Compound D: The same procedure of Example C for preparing compound C was followed with the exception of the use of  $\text{HfCl}_4$  in Part 4. Thus, when  
25        $[\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_3\text{C}_5)(\text{N-}\underline{\text{t}}\text{-Bu})]\text{Li}_2$  (3.29 g, 0.012 mol) and  $\text{HfCl}_4$  (4.0 g, 0.012 mol) were used, the product of the empirical formula  $\text{Me}_2\text{Si}(\underline{\text{t}}\text{-BuH}_3\text{C}_5)(\text{N-}\underline{\text{t}}\text{-Bu})\text{HfCl}_2$  (1.86 g, 0.0037 mol) was produced.

-29-

Example E

Compound E: Part 1.  $\text{Me}_2\text{SiCl}_2$  (7.0 g, 0.054 mol) was diluted with ~100 ml of ether.  $\text{Me}_3\text{SiC}_5\text{H}_4\text{Li}$  (5.9 g, 0.041 mol) was slowly added. Approximately 75 ml of  
5 thf was added and the mixture was allowed to stir overnight. The solvent was removed via a vacuum to a cold trap held at  $-196^\circ\text{C}$ . Pentane was added to precipitate out the  $\text{LiCl}$ . The mixture was filtered through Celite. The solvent was removed from the  
10 filtrate giving  $\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_4)\text{Cl}$  (8.1 g, 0.035 mol) as a pale yellow liquid.

Part 2.  $\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_4)\text{Cl}$  (3.96 g, 0.017 mol) was diluted with ~50 ml of ether.  $\text{LiHN-t-Bu}$  (1.36 g, 0.017 mol) was slowly added, and the mixture was  
15 allowed to stir overnight. The ether was removed via a vacuum and pentane was added to precipitate the  $\text{LiCl}$ . The mixture was filtered through Celite, and the pentane was removed from the filtrate.  $\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_4)(\text{NH-t-Bu})$  (3.7 g, 0.014 mol) was isolated as  
20 a pale yellow liquid.

Part 3.  $\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_4)(\text{NH-t-Bu})$  (3.7 g, 0.014 mol) as diluted with ether.  $\text{MeLi}$  (25 ml, 1.4 M in ether, 0.035 mol) was slowly added. The mixture was  
25 allowed to stir for 1.5 hours after the final addition of  $\text{MeLi}$ . The ether was removed via vacuum producing 4.6 g of a white solid formulated as  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_3)(\text{N-t-Bu})] \cdot 3/4\text{Et}_2\text{O}$  and unreacted  $\text{MeLi}$  which was not removed from the solid.

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_3\text{SiC}_5\text{H}_3)(\text{N-t-Bu})] \cdot 3/4\text{Et}_2\text{O}$   
30 (1.44 g, 0.0043 mol) was suspended in ~50 ml of ether.

-30-

ZrCl<sub>4</sub> (1.0 g, 0.0043 mol) was slowly added and the reaction was allowed to stir for a few hours. The solvent was removed via vacuum and pentane was added to precipitate the LiCl. The mixture was filtered  
5 through Celite, and the filtrate was reduced in volume. The flask was placed in the freezer (-40°C) to maximize precipitation of the product. The solid was filtered off giving 0.273 g of an off white solid. The filtrate was again reduced in volume, the precipitate  
10 filtered off to give an additional 0.345 g for a total of 0.62 g of the compound with empirical formula Me<sub>2</sub>Si(Me<sub>3</sub>SiC<sub>5</sub>H<sub>3</sub>)-  
(N-t-Bu)ZrCl<sub>2</sub>. The x-ray crystal structure of this product reveals that the compound is dimeric in  
15 nature.

#### Example F

Compound F: Part 1. Me<sub>4</sub>HC<sub>5</sub>SiMe<sub>2</sub>Cl was prepared as described in Example A for the preparation of compound A, Part 1.

20 Part 2. LiHNPh (4.6 g, 0.0462 mol) was dissolved in ~100 ml of thf. Me<sub>4</sub>HC<sub>5</sub>SiMe<sub>2</sub>Cl (10.0 g, 0.0466 mol) was slowly added. The mixture was allowed to stir overnight. The thf was removed via a vacuum. Petroleum ether and toluene were added to precipitate  
25 the LiCl, and the mixture was filtered through Celite. The solvent was removed, leaving behind a dark yellow liquid, Me<sub>2</sub>Si(Me<sub>4</sub>HC<sub>5</sub>)(NHPH) (10.5 g, 0.0387 mol).

Part 3. Me<sub>2</sub>Si(Me<sub>4</sub>HC<sub>5</sub>)(NHPH) (10.5g, 0.0387 mol) was diluted with ~60 ml of ether. MeLi (1.4 M in  
30 ether, 56 ml, 0.0784 mol) was slowly added and the



-31-

reaction was allowed to stir overnight. The resulting white solid,  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh}) \cdot 3/4\text{Et}_2\text{O}]$  (11.0 g), was filtered off and was washed with ether.

5       Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh}) \cdot 3/4\text{Et}_2\text{O}]$  (2.81 g, 0.083 mol) was suspended in ~40 ml of ether.  $\text{ZrCl}_4$  (1.92 g, 0.0082 mol) was slowly added and the mixture was allowed to stir overnight. The ether was removed via a vacuum, and a mixture of petroleum ether and toluene was added to precipitate the  $\text{LiCl}$ . The mixture  
10       was filtered through Celite, the solvent mixture was removed via vacuum, and pentane was added. The mixture was placed in the freezer at  $-40^\circ\text{C}$  to maximize the precipitation of the product. The solid was then filtered off and washed with pentane.  
15        $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh})\text{ZrCl}_2 \cdot \text{Et}_2\text{O}$  was recovered as a pale yellow solid (1.89 g).

#### Example G

Compound G: The same procedure of Example F for preparing compound F was followed with the exception  
20       of the use of  $\text{HfCl}_4$  in place of  $\text{ZrCl}_4$  in Part 4. Thus, when  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh})] \cdot 3/4\text{Et}_2\text{O}$  (2.0 g, 0.0059 mol) and  $\text{HfCl}_4$  (1.89 g, 0.0059 mol) were used,  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NPh})\text{HfCl}_2 \cdot 1/2\text{Et}_2\text{O}$  (1.70 g) was produced.

#### Example H

25       Compound H: Part 1.  $\text{MePhSiCl}_2$  (14.9 g, 0.078 mol) was diluted with ~250 ml of thf.  $\text{Me}_4\text{C}_5\text{HLi}$  (10.0 g, 0.078 mol) was slowly added as a solid. The reaction solution was allowed to stir overnight. The solvent was removed via a vacuum to a cold trap held at  
30        $-196^\circ\text{C}$ . Petroleum ether was added to precipitate out

-32-

the LiCl. The mixture was filtered through Celite, and the pentane was removed from the filtrate. MePhSi(Me<sub>4</sub>C<sub>5</sub>H)Cl (20.8 g, 0.075 mol) was isolated as a yellow viscous liquid.

5           Part 2. LiHN-t-Bu (4.28 g, 0.054 mol) was dissolved in ~100 ml of thf. MePhSi(Me<sub>4</sub>C<sub>5</sub>H)Cl (15.0 g, 0.054 mol) was added drop wise. The yellow solution was allowed to stir overnight. The solvent was removed via vacuum. Petroleum ether was added to precipitate  
10           out the LiCl. The mixture was filtered through Celite, and the filtrate was evaporated down. MePhSi(Me<sub>4</sub>C<sub>5</sub>H)(NH-t-Bu) (16.6 g, 0.053 mol) was recovered as an extremely viscous liquid.

          Part 3. MePhSi(Me<sub>4</sub>C<sub>5</sub>H)(NH-t-Bu) (16.6 g, 0.053  
15           mol) was diluted with ~100 ml of ether. MeLi (76 ml, 0.106 mol, 1.4 M) was slowly added and the reaction mixture was allowed to stir for ~3 hours. The ether was reduced in volume and the lithium salt was filtered off and washed with pentane producing 20.0 g  
20           of a pale yellow solid formulated as Li<sub>2</sub>[MePhSi(Me<sub>4</sub>C<sub>5</sub>)(N-t-Bu)]•3/4Et<sub>2</sub>O.

          Part 4. Li<sub>2</sub>[MePhSi(Me<sub>4</sub>C<sub>5</sub>)(N-t-Bu)]•3/4Et<sub>2</sub>O (5.0 g, 0.0131 mol) was suspended in ~100 ml of Et<sub>2</sub>O. ZrCl<sub>4</sub> (3.06 g, 0.0131 mol) was slowly added. The reaction  
25           mixture was allowed to stir at room temperature for ~1.5 hours over which time the reaction mixture slightly darkened in color. The solvent was removed via vacuum and a mixture of petroleum ether and toluene was added. The mixture was filtered through  
30           Celite to remove the LiCl. The filtrate was evaporated

-33-

down to near dryness and filtered off. The off white solid was washed with petroleum ether. The yield of product,  $\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{ZrCl}_2$ , was 3.82 g (0.0081 mol).

5

Example I

Compound I:  $\text{Li}_2[\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})] \cdot 3/4\text{Et}_2\text{O}$  was prepared as described in Example H for the preparation of compound H, Part 3.

10 Part 4.  $\text{Li}_2[\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})] \cdot 3/4\text{Et}_2\text{O}$  (5.00 g, 0.0131 mol) was suspended in ~100 ml of  $\text{Et}_2\text{O}$ .  $\text{HfCl}_4$  (4.20 g, 0.0131 mol) was slowly added and the reaction mixture was allowed to stir overnight. The solvent was removed via vacuum and petroleum ether was added to precipitate out the  $\text{LiCl}$ . The mixture was filtered  
15 through Celite. The filtrate was evaporated down to near dryness and filtered off. The off white solid was washed with petroleum ether.  $\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{HfCl}_2$  was recovered (3.54 g, 0.0058 mole).

Example J

20 Compound J:  $\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{HfMe}_2$  was prepared by adding a stoichiometric amount of  $\text{MeLi}$  (1.4 M in ether) to  $\text{MePhSi}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{HfCl}_2$  suspended in ether. The white solid could be isolated in near quantitative yield.

25

Example K

Compound K: Part 1.  $\text{Me}_4\text{C}_5\text{SiMe}_2\text{Cl}$  was prepared as described in Example A for the preparation of compound A, Part 1.

30 Part 2.  $\text{Me}_4\text{C}_5\text{SiMe}_2\text{Cl}$  (10.0 g, 0.047 mol) was diluted with ~25 ml  $\text{Et}_2\text{O}$ .  $\text{LiHNC}_5\text{H}_4\text{-p-n-Bu} \cdot 1/10\text{Et}_2\text{O}$

-34-

(7.57 g, 0.047 mol) was added slowly. The mixture was allowed to stir for ~3 hours. The solvent was removed via vacuum. Petroleum ether was added to precipitate out the LiCl, and the mixture was filtered through  
5 Celite. The solvent was removed leaving behind an orange viscous liquid,  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5\text{H})(\text{HNC}_6\text{H}_4\text{-p-n-Bu})$  (12.7 g, 0.039 mol).

Part 3.  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5\text{H})(\text{HNC}_6\text{H}_4\text{-p-n-Bu})$  (12.7 g, 0.039 mol) was diluted with ~50 ml of  $\text{Et}_2\text{O}$ . MeLi (1.4 M, 55 ml, 0.077 mol) was slowly added. The mixture was  
10 allowed to stir for ~3 hours. The product was filtered off and washed with  $\text{Et}_2\text{O}$  producing  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NC}_6\text{H}_4\text{-p-n-Bu})] \cdot 3/4\text{Et}_2\text{O}$  as a white solid (13.1 g, 0.033 mol).

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NC}_6\text{H}_4\text{-p-n-Bu})] \cdot 3/4\text{Et}_2\text{O}$  (3.45 g, 0.0087 mol) was suspended in ~50 ml of  $\text{Et}_2\text{O}$ .  $\text{ZrCl}_4$  (2.0 g, 0.0086 mol) was slowly added and the mixture was allowed to stir overnight. The ether was removed via vacuum, and petroleum ether was added to  
20 precipitate out the LiCl. The mixture was filtered through Celite. The filtrate was evaporated to dryness to give a yellow solid which was recrystallized from pentane and identified as  $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NC}_6\text{H}_4\text{-p-n-Bu})\text{ZrCl}_2 \cdot 3\text{Et}_2\text{O}$  (4.2 g).

25

Example L

Compound L:  $\text{Li}_2[\text{MeSi}(\text{Me}_4\text{C}_5)(\text{NC}_6\text{H}_4\text{-p-n-Bu})] \cdot 3/4\text{Et}_2\text{O}$  was prepared as described in Example K for the preparation of compound K, Part 3.

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{NC}_6\text{H}_4\text{-p-n-Bu})] \cdot 3/4\text{Et}_2\text{O}$  (3.77 g., 0.0095 mol) was suspended in ~50 ml of  $\text{Et}_2\text{O}$ .  
30

-35-

HfCl<sub>4</sub> (3.0 g, 0.0094 mol) was slowly added as a solid and the mixture was allowed to stir overnight. The ether was removed via vacuum and petroleum ether was added to precipitate out the LiCl. The mixture was  
5 filtered through Celite. Petroleum ether was removed via a vacuum giving an off white solid which was recrystallized from pentane. The product was identified as Me<sub>2</sub>Si(Me<sub>4</sub>C<sub>5</sub>)-(NC<sub>6</sub>H<sub>4</sub>-p-n-Bu)HfCl<sub>2</sub> (1.54 g, 0.0027 mol.).

10

EXAMPLE AT

Compound AT: Part 1. MePhSiCl<sub>2</sub> (14.9 g, 0.078 mol) was diluted with 250 ml of thf. Me<sub>4</sub>HC<sub>5</sub>Li (10.0 g, 0.078 mol) was slowly added as a solid. The reaction solution was allowed to stir overnight. The solvent  
15 was removed via a vacuum to a cold trap held at -196°C. Petroleum ether was added to precipitate out the LiCl. The mixture was filtered through Celite and the pentane was removed from the filtrate. MePhSi(Me<sub>4</sub>C<sub>5</sub>H)Cl (20.8 g, 0.075 mol) was isolated as a  
20 yellow viscous liquid.

Part 2. LiHN-t-Bu (4.28 g, 0.054 mol) was dissolved in ~100 ml of thf. MePhSi(C<sub>5</sub>Me<sub>4</sub>H)Cl (15.0 g, 0.054 mol) was added dropwise. The yellow solution was allowed to stir overnight. The solvent was  
25 removed in vacuo. Petroleum ether was added to precipitate the LiCl. The mixture was filtered through Celite, and the filtrate was evaporated. MePhSi(C<sub>5</sub>Me<sub>4</sub>H)(NH-t-Bu) (16.6 g, 0.053 mol) was recovered as an extremely viscous liquid.

-36-

Part 3.  $\text{MePhSi}(\text{C}_5\text{Me}_4\text{H})(\text{NH}-t\text{-Bu})$  (17.2 g, 0.055 mol) was diluted with ~20 ml of ether.  $n\text{-BuLi}$  (60 ml in hexane, 0.096 mol, 1.6 M) was slowly added and the reaction mixture was allowed to stir for ~3 hours. The solvent was removed in vacuo to yield 15.5 g (0.48 mol) of a pale tan solid formulated as  $\text{Li}_2[\text{MePhSi}(\text{C}_5\text{Me}_4)(\text{N}-t\text{-Bu})]$ .

Part 4.  $\text{Li}_2[\text{MePhSi}(\text{C}_5\text{Me}_4)(\text{N}-t\text{-Bu})]$  (8.75 g, 0.027 mol) was suspended in ~125 ml of cold ether (~-30°C).  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$  (9.1 g, 0.027 mol) was slowly added. The reaction was allowed to stir for several hours prior to removing the ether via vacuum. A mixture of toluene and dichloromethane was then added to solubilize the product. The mixture was filtered through Celite to remove the  $\text{LiCl}$ . The solvent was largely removed via vacuum and petroleum ether was added. The mixture was cooled to maximize product precipitation. The crude product was filtered off and redissolved in toluene. The toluene insolubles were filtered off. The toluene was then reduced in volume and petroleum ether was added. The mixture was cooled to maximize precipitation prior to filtering off 3.34 g (7.76 mmol) of the yellow solid  $\text{MePhSi}(\text{C}_5\text{Me}_4)(\text{N}-t\text{-Bu})\text{TiCl}_2$ .

#### EXAMPLE BT

Compound BT: Part 1.  $\text{C}_5\text{Me}_4\text{HLi}$  (10.0 g, 0.078 mol) was slowly added to a  $\text{Me}_2\text{SiCl}_2$  solution (11.5 ml, 0.095 mol, in 225 ml of tetrahydrofuran). The solution was stirred for 1 hour to assure a complete reaction. The solvent was then removed in vacuo.

-37-

Pentane was added to precipitate the LiCl. The mixture was filtered through Celite and the solvent was removed from the filtrate in vacuo.  $(C_5Me_4H)SiMe_2Cl$  (15.34 g, 0.071 mol) was recovered as a pale yellow liquid.

Part 2.  $(C_5Me_4H)SiMe_2Cl$  (10.0 g, 0.047 mol) was diluted with ~25 ml of  $Et_2O$ .  $LiHNC_5H_4-p-n-Bu \cdot 1/10Et_2O$  (7.75 g, 0.048 mol) was added slowly. The mixture was allowed to stir for ~3 hours. The solvent was removed in vacuo. Petroleum ether was added to precipitate the LiCl, and the mixture was filtered through Celite. The solvent was removed leaving behind an orange viscous liquid,  $Me_2Si(C_5Me_4H)(HNC_6H_4-p-n-Bu)$  (12.7 g, 0.039 mol). Part 3.  $Me_2Si(C_5Me_4H)(HNC_6H_4-p-n-Bu)$  (12.7 g, 0.039 mol) was diluted with ~50 ml of  $Et_2O$ . MeLi (1.4 M, 55 ml, 0.077 mol) was slowly added. The mixture was allowed to stir for ~3 hours. The product was filtered off and washed with  $Et_2O$  and dried.  $Li_2[Me_2Si(C_5Me_4)(NC_6H_4-p-n-Bu)] \cdot 3/4Et_2O$  was isolated as a white solid (13.1 g, 0.033 mol).

Part 4.  $Li_2[Me_2Si(C_5Me_4)(NC_6H_4-p-n-Bu)] \cdot 3/4Et_2O$  (2.36 g, 5.97 mmol) was suspended in cold ether.  $TiCl_4 \cdot 2Et_2O$  (2.0g, 5.92 mmol) was slowly added. The mixture was allowed to stir overnight. The solvent was removed via vacuum and petroleum ether and dichloromethane were added. The mixture was filtered through Celite to remove the LiCl. The solvent was removed via vacuum, and toluene and petroleum ether were added. After refrigeration, the mixture was filtered off, producing an off yellow product. This

-38-

was redissolved in dichloromethane, followed by the addition of petroleum ether. The mixture was then refrigerated prior to filtering off 0.83 g (1.87 mmol) of the yellow solid,  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_6\text{H}_4\text{-p-n-Bu})\text{TiCl}_2$ .

5

EXAMPLE CT

Compound CT: Part 1.  $(\text{C}_5\text{Me}_4\text{H})\text{SiMe}_2\text{Cl}$  was prepared as described in Example BT for the preparation of compound BT, Part 1.

Part 2.  $(\text{C}_5\text{Me}_4\text{H})\text{SiMe}_2\text{Cl}$  (8.14 g, 0.038 mol) was mixed with ~100 ml of thf.  $\text{LiHNC}_6\text{H}_4\text{-p-OMe}$  (4.89 g, 0.038 mol) was slowly added and the mixture was allowed to stir for 2 hours. The solvent was removed via vacuum and petroleum ether was added to precipitate the LiCl which was filtered off. The solvent was removed from the filtrate via vacuum and the product  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4\text{H})(\text{NC}_6\text{H}_4\text{-p-OMe})$  (9.8 g, 0.033 mol) was isolated as a viscous orange-yellow liquid.

15

Part 3.  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4\text{H})(\text{HNC}_6\text{H}_4\text{-p-OMe})$  (10.0 g, 0.033 mol) was diluted with thf.  $\text{MeLi}$  (47 ml, 1.4 M in ether, 0.066 mol) was slowly added and the mixture was allowed to stir for a few hours. The solvent was then removed in vacuo leaving behind a white solid coordinated by thf. The product was formulated as  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_6\text{H}_4\text{-p-OMe})]\cdot 2\text{thf}$  (14.7 g, 0.032 mol).

25

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_6\text{H}_4\text{-p-OMe})]\cdot 2\text{thf}$  (7.0 g, 0.015 mol) was suspended in ~125 ml of cold ether.  $\text{TiCl}_4\cdot 2\text{Et}_2\text{O}$  (5.1 g, 0.015 mol) was slowly added and the mixture was allowed to stir overnight. The solvent was removed via vacuum and petroleum ether,

30



-39-

dichloromethane and toluene were added. The mixture was filtered through Celite to remove the LiCl. The solvent was reduced in volume and petroleum ether was added. The mixture was refrigerated, after which a brown solid was filtered off. Multiple extractions and recrystallizations from toluene and petroleum ether yielded 2.3 g (5.5 mmol) of  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_6\text{H}_4\text{-p-OMe})\text{TiCl}_2$ .

EXAMPLE DT

10        Compound DT: Part 1.  $\text{Me}_2\text{SiCl}_2$  (7.5 ml, 0.062 mol) was diluted with ~30 ml of thf. A  $t\text{-BuH}_4\text{C}_5\text{Li}$  solution (7.29 g, 0.057 mol, ~100 ml of thf) was slowly added, and the resulting mixture was allowed to stir overnight. The thf was removed in vacuo. Pentane was added to precipitate the LiCl, and the mixture was filtered through Celite. The pentane was removed from the filtrate leaving behind a pale yellow liquid,  $(t\text{-BuC}_5\text{H}_4)\text{SiMe}_2\text{Cl}$  (10.4 g, 0.048 mol).

15        Part 2.  $(t\text{-BuC}_5\text{H}_4)\text{SiMe}_2\text{Cl}$  (5.0 g, 0.023 mol) was added to ~50 ml of thf.  $\text{LiHN-2,5-}t\text{-Bu}_2\text{C}_6\text{H}_3$  (4.94 g, 0.023 mol) was slowly added and the reaction mixture was allowed to stir for 2 hours. The solvent was removed via vacuum and petroleum ether was added to precipitate the LiCl which was filtered off. The solvent was removed from the filtrate yielding an oily/solid material,  $\text{Me}_2\text{Si}(t\text{-Bu}_2\text{C}_5\text{H}_4)(\text{HN-2,5-}t\text{-Bu}_2\text{C}_6\text{H}_3)$ .

25        Part 3. To the above material,  $\text{Me}_2\text{Si}(t\text{-BuC}_5\text{H}_4)(\text{HN-2,5-}t\text{-Bu}_2\text{C}_6\text{H}_3)$  (assumed to be ~8 g, 0.021 mol), MeLi (30 ml, 1.4 M in ether, 0.042 mol) was

30

-40-

slowly added. The mixture was allowed to stir for a few hours prior to removing the solvent via vacuum. The slightly pinkish solid was washed with ether, filtered and dried yielding 4.42 g (0.011 mol) of

5  $\text{Li}_2[\text{Me}_2\text{Si}(\text{t-BuC}_5\text{H}_3)(\text{N-2,5-t-Bu}_2\text{C}_6\text{H}_3)]$ .

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{t-BuC}_5\text{H}_3)(\text{N-2,5-t-Bu}_2\text{C}_6\text{H}_3)]$  (7.6 g, 0.019 mol) was suspended in cold ether.  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$  (6.5 g, 0.019 mol) was slowly added and the mixture was allowed to stir overnight. The solvent was

10 removed via vacuum and toluene and dichloromethane were added. The mixture was filtered through Celite to remove the  $\text{LiCl}$ . The filtrate was reduced in volume and petroleum ether was added. The mixture was chilled to maximize precipitation. A dark yellow

15 solid was filtered off and was recrystallized from toluene and petroleum ether giving a tan solid. A total of 1.6 g (3.2 mmol) of  $\text{Me}_2\text{Si}(\text{t-BuC}_5\text{H}_3)(\text{N-2,5-t-Bu}_2\text{C}_6\text{H}_3)\text{TiCl}_2$  was isolated.

#### EXAMPLE ET

20 Compound ET: Part 1.  $\text{LiC}_9\text{H}_7$  (40 g, 0.33 mol, lithiated indene =  $\text{Li}(\text{Hind})$ ) was slowly added to  $\text{Me}_2\text{SiCl}_2$  (60 ml, 0.49 mol) in ether and thf. The reaction was allowed to stir for 1.5 hours prior to removing the solvent via vacuum. Petroleum ether was

25 then added, and the  $\text{LiCl}$  was filtered off. The solvent was removed from the filtrate via vacuum, leaving behind the pale yellow liquid,  $(\text{Hind})\text{Me}_2\text{SiCl}$  (55.7 g, 0.27 mol).

Part 2.  $(\text{Hind})\text{Me}_2\text{SiCl}$  (20.0 g, 0.096 mol) was

30 diluted with ether.  $\text{LiHN-t-Bu}$  (7.6 g, 0.096 mol) was

-41-

slowly added and the mixture was allowed to stir overnight. The solvent was removed via vacuum and petroleum ether and toluene were added. The LiCl was filtered off and the solvent was removed via vacuum to give the product,  $\text{Me}_2\text{Si}(\text{Hind})(\text{HN-t-Bu})$ .

5           Part 3.  $\text{Me}_2\text{Si}(\text{Hind})(\text{HN-t-Bu})$  (21 g, 0.086 mol) was diluted with a mixture of petroleum ether and diethyl ether.  $\text{t-BuLi}$  (108 ml, 1.6 M in hexanes, 0.17 mol) was slowly added and the mixture was allowed to stir overnight. The solvent was removed via vacuum and the remaining solid was washed with petroleum ether and filtered off.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{ind})(\text{N-t-Bu})] \cdot 1/4\text{Et}_2\text{O}$  was isolated as a pale yellow solid (26 g, 0.094 mol).

15           Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{ind})(\text{N-t-Bu})] \cdot 1/4\text{Et}_2\text{O}$  (10 g, 0.036 mol) was dissolved in ether.  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$  (12.1 g, 0.036 mol) was added to the cold solution. The reaction was allowed to stir overnight prior to removal of the solvent via vacuum. A mixture of toluene and dichloromethane were added and the mixture was filtered through Celite to remove the LiCl. The solvent was removed and hot toluene was added. The insolubles were filtered off. The solution was reduced in volume and petroleum ether was added. The mixture was chilled prior to filtering off the solid,  $\text{Me}_2\text{Si}(\text{ind})(\text{N-t-Bu})\text{TiCl}_2$ , which was recrystallized several times. The final yield was 2.5 g (6.8 mmol).

-42-

EXAMPLE FT

Compound FT: Part 1.  $(C_5Me_4H)SiMe_2Cl$  was prepared as described in Example BT for the preparation of compound BT, Part 1.

5 Part 2.  $(C_5Me_4H)SiMe_2Cl$  (5.19 g, 0.024 mol) was slowly added to a solution of  $LiHNC_6H_{11}$  (2.52 g, 0.024 mol) in ~125 ml of thf. The solution was allowed to stir for several hours. The thf was removed via vacuum and petroleum ether was added to precipitate  
10 the  $LiCl$  which was filtered off. The solvent was removed from the filtrate via vacuum yielding 6.3 g (0.023 mol) of the yellow liquid,  $Me_2Si(C_5Me_4H)(HNC_6H_{11})$ .

15 Part 3.  $Me_2Si(C_5Me_4H)(HNC_6H_{11})$  (6.3 g, 0.023 mol) was diluted with ~100 ml of ether.  $MeLi$  (33 ml, 1.4 M in ether, 0.046 mol) was slowly added and the mixture was allowed to stir for 0.5 hours prior to filtering off the white solid. The solid was washed with ether and vacuum dried.  $Li_2[Me_2Si(C_5Me_4)(NC_6H_{11})]$   
20 was isolated in a 5.4 g (0.019 mol) yield.

25 Part 4.  $Li_2[Me_2Si(C_5Me_4)(NC_6H_{11})]$  (2.57 g, 8.90 mmol) was suspended in ~50 ml of cold ether.  $TiCl_4 \cdot 2Et_2O$  (3.0 g, 8.9 mmol) was slowly added and the mixture was allowed to stir overnight. The solvent  
30 was removed via vacuum and a mixture of toluene and dichloromethane was added. The mixture was filtered through Celite to remove the  $LiCl$  byproduct. The solvent was removed from the filtrate and a small portion of toluene was added followed by petroleum ether. The mixture was chilled in order to maximize

-43-

precipitation. A brown solid was filtered off which was initially dissolved in hot toluene, filtered through Celite, and reduced in volume. Petroleum ether was then added. After refrigeration, an olive green solid was filtered off. This solid was recrystallized twice from dichloromethane and petroleum ether to give a final yield of 0.94 g (2.4 mmol) of the pale olive green solid,  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_6\text{H}_{11})\text{TiCl}$ .

EXAMPLE GT

Compound GT: Part 1.  $\text{Me}_2\text{SiCl}_2$  (150 ml, 1.24 mol) was diluted with ~200 ml of  $\text{Et}_2\text{O}$ .  $\text{Li}(\text{C}_{13}\text{H}_9)\cdot\text{Et}_2\text{O}$  (lithiated fluorene etherate, 28.2 g, 0.11 mol) was slowly added. The reaction was allowed to stir for ~1 hour prior to removing the solvent via vacuum. Toluene was added and the mixture was filtered through Celite to remove the  $\text{LiCl}$ . The solvent was removed from the filtrate, leaving behind the off-white solid,  $\text{Me}_2\text{Si}(\text{C}_{13}\text{H}_9)\text{Cl}$  (25.4 g, 0.096 mol).

Part 2.  $\text{Me}_2\text{Si}(\text{C}_{13}\text{H}_9)\text{Cl}$  (8.0 g, 0.031 mol) was suspended in ether and thf in a ratio of 5:1.  $\text{LiHNC}_6\text{H}_{11}$  (3.25 g, 0.031 mol) was slowly added. The reaction mixture was allowed to stir overnight. After removal of the solvent via vacuum, toluene was added and the mixture was filtered through Celite to remove the  $\text{LiCl}$ . The filtrate was reduced in volume to give a viscous orange liquid. To this liquid which was diluted in  $\text{Et}_2\text{O}$ , 43 ml of 1.4 M  $\text{MeLi}$  (0.060 mol) was added slowly. The mixture was allowed to stir overnight. The solvent was removed in vacuo to

-44-

produce 13.0 g (0.031 mol) of  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_{13}\text{H}_8)(\text{NC}_6\text{H}_{11})] \cdot 1.25 \text{ Et}_2\text{O}$ .

Part 3.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_{13}\text{H}_8)(\text{NC}_6\text{H}_{11})] \cdot 1.25 \text{ Et}_2\text{O}$  (6.5 g, 0.015 mol) was dissolved in cold ether.  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$  (5.16 g, 0.015 mol) was slowly added. The mixture was allowed to stir overnight. The solvent was removed via vacuum and methylene chloride was added. The mixture was filtered through Celite to remove the  $\text{LiCl}$ . The filtrate was reduced in volume and petroleum ether was added. This was refrigerated to maximize precipitation prior to filtering off the solid. Since the solid collected was not completely soluble in toluene, it was mixed with toluene and filtered. The filtrate was reduced in volume and petroleum ether was added to induce precipitation. The mixture was refrigerated prior to filtration. The red-brown solid  $\text{Me}_2\text{Si}(\text{C}_{13}\text{H}_8)(\text{NC}_6\text{H}_{11})\text{TiCl}_2$  was isolated (2.3 g, 5.2 mol).

#### EXAMPLE HT

Compound HT: Part 1.  $(\text{C}_5\text{Me}_4\text{H})\text{SiMe}_2\text{Cl}$  was prepared as described in Example BT for the preparation of compound BT, Part 1.

Part. 2  $\text{LiHNPh}$  (4.6 g, 0.046 mol) was dissolved in ~100 ml of thf.  $(\text{C}_5\text{Me}_4\text{H})\text{SiMe}_2\text{Cl}$  (10.0 g, 0.047 mol) was slowly added. The mixture was allowed to stir overnight. The thf was removed in vacuo. Petroleum ether and toluene were added to precipitate the  $\text{LiCl}$ , and the mixture was filtered through Celite. The solvent was removed, leaving behind a dark yellow liquid,  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4\text{H})(\text{NHPh})$  (10.5 g, 0.039 mol).

-45-

Part 3.  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4\text{H})(\text{NPh})$  (9.33 g, 0.034 mol) was diluted with ~30 ml of ether.  $\text{MeLi}$  (1.4 M in ether, 44 ml, 0.062 mol) was slowly added and the reaction was allowed to stir for 2 hours. After  
5 reducing the volume of the solvent, the resulting white solid,  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NPh})] \cdot 1/2\text{Et}_2\text{O}$  (9.7 g, 0.030 mol), was filtered off washed with ether and dried.

Part 4.  $\text{Li}_2[\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NPh})] \cdot 1/2\text{Et}_2\text{O}$  (4.3 g, 0.013 mol) was suspended in ~50 ml of cold ether.  
10  $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$  (4.10 g, 0.012 mol) was slowly added, and the mixture was allowed to stir for several hours. The solvent was removed in vacuo, and toluene and dichloromethane were added to solubilize the product.  
15 The mixture was filtered through Celite to remove the  $\text{LiCl}$ . The solvent was removed in vacuo and a small portion of toluene was added along with petroleum ether. The mixture was refrigerated in order to  
20 maximize precipitation of a tan solid which was filtered off. The solid was washed with a small portion of toluene and the remaining solid was redissolved in hot toluene and filtered through Celite to remove the toluene insolubles. The toluene was  
25 then removed to produce 2.32 g (5.98 mmol) of the yellow solid,  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NPh})\text{TiCl}_2$ .

#### EXAMPLE IT

Compound IT: Part 1.  $(\text{C}_5\text{Me}_4\text{H})\text{SiMe}_2\text{Cl}$  was prepared as described in Example BT for the preparation of Compound BT, part 1.

-46-

Part 2.  $(C_5Me_4H)SiMe_2Cl$  (10.0 g, 0.047 mol) was slowly added to a suspension of  $LiHN-t-Bu$  (3.68 g, 0.047 mol, -100 ml thf). The mixture was stirred overnight. The thf was then removed via a vacuum to  
5 a cold trap held at  $-196^\circ C$ . Petroleum ether was added to precipitate out the  $LiCl$ . The mixture was filtered through Celite. The solvent was removed from the filtrate.  $Me_2Si(C_5Me_4H)(NH-t-Bu)$  (11.14 g, 0.044 mol) was isolated as a pale yellow liquid.

10 Part 3.  $Me_2Si(C_5Me_4H)(NH-t-Bu)$  (11.14 g, 0.044 mol) was diluted with -100 ml of ether.  $MeLi$  (1.4 M, 64 ml, 0.090 mol) was slowly added. The mixture was allowed to stir for 1/2 hour after the final addition of  $MeLi$ . The ether was reduced in volume prior to  
15 filtering off the product. The product,  $[Me_2Si(C_5Me_4)(N-t-Bu)]Li_2$ , was washed with several small portions of ether, then vacuum dried.

Part 4.  $[Me_2Si(C_5Me_4)(N-t-Bu)]Li_2$  (6.6 g, 0.025 mol) was suspended in cold ether.  $TiCl_4 \cdot 2Et_2O$  (8.4 g, 0.025 mol) was slowly added and the resulting mixture was allowed to stir overnight. The ether was removed  
20 via a vacuum to a cold trap held at  $-196^\circ C$ . Methylene chloride was added to precipitate out the  $LiCl$ . The mixture was filtered through Celite. The solvent was significantly reduced in volume and petroleum ether  
25 was added to precipitate out the product. This mixture was refrigerated prior to filtration in order to maximize precipitation.  $Me_2Si(C_5Me_4)(N-t-Bu)TiCl_2$  was isolated (2.1 g, 5.7 mmol).



-47-

EXAMPLE JT

Compound JT: Part 1.  $(C_5Me_4H)SiMe_2Cl$  was prepared as described in Example BT for the preparation of Compound BT, Part 1.

5 Part 2.  $(C_5Me_4H)SiMe_2Cl$  (8.0 g, 0.037 mol) was slowly added to a suspension of  $LiHNC_{12}H_{23}$  ( $C_{12}H_{23}$ =cyclododecyl, 7.0 g, 0.037 mol, -80 ml thf). The mixture was stirred overnight. The thf was then removed via a vacuum to a cold trap held at  $-196^\circ C$ .  
10 Petroleum ether and toluene was added to precipitate out the  $LiCl$ . The mixture was filtered through Celite. The solvent was removed from the filtrate.  $Me_2Si(C_5Me_4H)(NHC_{12}H_{23})$  (11.8 g, 0.033 mol) was isolated as a pale yellow liquid.

15 Part 3.  $Me_2Si(C_5Me_4H)(NHC_{12}H_{23})$  (11.9 g, 0.033 mol) was diluted with ~150 ml of ether.  $MeLi$  (1.4 M, 47 ml, 0.066 mol) was slowly added. The mixture was allowed to stir for 2 hours after the final addition of  $MeLi$ . The ether was reduced in volume prior to  
20 filtering off the product. The product,  $[Me_2Si(C_5Me_4)(NC_{12}H_{23})]Li_2$ , was washed with several small portions of ether, then vacuum dried to yield 11.1 g (0.030 mol) of product.

25 Part 4.  $[Me_2Si(C_5Me_4)(NC_{12}H_{23})]Li_2$  (3.0 g, 0.008 mol) was suspended in cold ether.  $TiCl_4 \cdot 2Et_2O$  (2.7 g, 0.008 mol) was slowly added and the resulting mixture was allowed to stir overnight. The ether was removed via a vacuum to a cold trap held at  $-196^\circ C$ . Methylene chloride was added to precipitate out the  $LiCl$ . The  
30 mixture was filtered through Celite. The solvent was

-48-

significantly reduced in volume and petroleum ether was added to precipitate out the product. This mixture was refrigerated prior to filtration in order to maximize precipitation. The solid collected was  
5 recrystallized from methylene chloride and  $\text{Me}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{NC}_{12}\text{H}_{23})\text{TiCl}_2$  was isolated (1.0 g, 2.1 mmol).

### Examples 1-70 of Polymerization

#### EXAMPLE 1

#### 10 Polymerization - Compound A

The polymerization run was performed in a 1-liter autoclave reactor equipped with a paddle stirrer, an external water jacket for temperature control, a regulated supply of dry nitrogen, ethylene, propylene,  
15 1-butene and hexane, and a septum inlet for introduction of other solvents, transition metal compound and alumoxane solutions. The reactor was dried and degassed thoroughly prior to use. A typical run consisted of injecting 400 ml of toluene, 6 ml of  
20 1.5 M MAO, and 0.23 mg of compound A (0.2 ml of a 11.5 mg in 10 ml of toluene solution) into the reactor. The reactor was then heated to 80°C and the ethylene (60 psi) was introduced into the system. The solvent was evaporated off of the polymer by a stream of  
25 nitrogen. Polyethylene was recovered (9.2 g, MW = 257,200, MWD = 2.275).

#### EXAMPLE 2

#### Polymerization Compound A

The polymerization was carried out as in Example  
30 1 with the following changes: 300 ml of toluene, 3 ml

-49-

of 1.5 M MAO, and 0.115 mg of compound A (0.1 ml of a 11.5 mg in 10 ml of toluene solution). Polyethylene was recovered (3.8 g, MW = 359,800, MWD = 2.425).

### EXAMPLE 3

#### 5 Polymerization - Compound A

The polymerization was carried out as in Example 2 using the identical concentrations. The difference involved running the reaction at 40°C rather than 80°C as in the previous example. Polyethylene was recovered (2.4 g, MW = 635,000, MWD = 3.445).

### EXAMPLE 4

#### 15 Polymerization - Compound A

The polymerization was carried out as in Example 1 except for the use of 300 ml of hexane in place of 400 ml of toluene. Polyethylene was recovered (5.4 g, MW = 212,600, MWD = 2.849).

### EXAMPLE 5

#### 20 Polymerization - Compound A

Using the same reactor design and general procedure as in Example 1, 300 ml of toluene, 200 ml of propylene, 6.0 ml of 1.5 M MAO, and 0.46 mg of compound A (0.4 ml of a 11.5 mg in 10 ml of toluene solution) was introduced into the reactor. The reactor was heated to 80°C, the ethylene was added (60 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 13.3 g of an ethylene-propylene copolymer was recovered (MW = 24,900, MWD = 2.027, 73.5 SCB/1000C by IR).

-50-

EXAMPLE 6Polymerization - Compound A

5 The polymerization was carried out as in Example 5 except with the following changes: 200 ml of toluene and 0.92 mg of compound A (0.8 ml of a 11.5 mg in 10 ml of toluene solution). The reaction temperature was also reduce to 50°C. An ethylene-propylene copolymer was recovered (6.0 g, MW = 83,100, MWD = 2.370, 75.7 SCB/1000C by IR).

EXAMPLE 7

10

Polymerization - Compound A

Using the same reactor design and general procedure as in Example 1, 150 ml of toluene, 100 ml of 1-butene, 6.0 ml of 1.5 M MAO, and 2.3 mg of  
15 compound A (2.0 ml of a 11.5 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 50°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system.  
20 After evaporation of the toluene, 25.4 g of an ethylene-1-butene copolymer was recovered (MW = 184,500, MWD = 3.424, 23.5 SCB/1000C by <sup>13</sup>C NMR and 21.5 SCB/1000C by IR).

EXAMPLE 825 Polymerization - Compound A

The polymerization was carried out as in Example 7 except with the following changes: 100 ml of toluene and 150 ml of 1-butene. An ethylene-1-butene copolymer was recovered (30.2 g, MW = 143,500, MWD = 3.097, 30.8  
30 SCB/1000C by <sup>13</sup>C NMR and 26.5 SCB/1000C by IR).

-51-

EXAMPLE 9Polymerization - Compound A

5 The polymerization was carried out as in Example 7 except with the following changes: 200 ml of toluene, 8.0 ml of 1.0 M MAO, and 50 ml of 1-butene. An ethylene-1-butene copolymer was recovered (24.9 g, MW = 163,200, MWD = 3.290, 23.3 SCB/1000C by  $^{13}\text{C}$  NMR and 18.9 SCB/1000C by IR).

EXAMPLE 10

10 Polymerization - Compound A

The polymerization was carried out as in Example 9 except for the replacement of 200 ml of toluene with 200 ml of hexane. An ethylene-1-butene copolymer was recovered (19.5 g, MW = 150,600, MWD = 3.510, 12.1 SCB/1000C by  $^{13}\text{C}$  NMR and 12.7 SCB/1000C by IR).

EXAMPLE 11Polymerization - Compound A

20 The polymerization was carried out as in Example 10 except with the following changes: 150 ml of hexane, and 100 ml of 1-butene. An ethylene-1-butene copolymer was recovered (16.0 g, MW = 116,200, MWD = 3.158, 19.2 SCB/1000C by  $^{13}\text{C}$  NMR and 19.4 SCB/1000C by IR).

EXAMPLE 12

25 Polymerization - Compound A

Using the same reactor design and general procedure as described in Example 1, 400 ml of toluene, 5.0 ml of 1.0 M MAO, and 0.2 ml of a preactivated compound A solution (11.5 mg of compound A dissolved in 9.0 ml of toluene and 1.0 ml of 1.0 M

30

-52-

MAO) were added to the reactor. The reactor was heated to 80°C, and ethylene was introduced (60 psi), and the reactor was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 3.4 g of polyethylene was recovered (MW = 285,000, MWD = 2.808).

#### EXAMPLE 13

##### Polymerization - Compound A

A polymerization was carried out as in Example 12 with exception of aging the preactivated compound A solution by one day. Polyethylene was recovered (2.0 g, MW = 260,700, MWD = 2.738).

#### EXAMPLE 14

##### Polymerization - Compound A

Using the same reactor design and general procedure as described in Example 1, 400 ml of toluene, 0.25 ml of 1.0 M MAO, and 0.2 ml of a preactivated compound A solution (11.5 mg of compound A dissolved in 9.5 ml of toluene and 0.5 ml of 1.0 M MAO) were added into the reactor. The reactor was heated to 80°C and ethylene was introduced (60 psi), and the reactor was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 1.1 g of polyethylene was recovered (MW = 479,600, MWD = 3.130).

#### EXAMPLE 15

##### Polymerization - Compound A

Using the same reactor design and general procedure as described in Example 1, 400 ml of toluene

-53-

and 2.0 ml of a preactivated compound A solution (11.5 mg of compound A dissolved in 9.5 ml of toluene and 0.5 ml of 1.0 M MAO) were added into the reactor. The reactor was heated to 80°C and ethylene was introduced (60 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 1.6 g of polyethylene was recovered (MW = 458,800, MWD = 2.037).

#### EXAMPLE 16

##### Polymerization - Compound A

Using the general procedure as described in Example 1, 400 ml of toluene, 5.0 ml of 1.0 M MAO, 0.23 mg of compound A (0.2 ml of a 11.5 mg in 10 ml of toluene solution) was added to the reactor. The reactor was heated to 80°C, the ethylene introduced (400 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 19.4 g of polyethylene was recovered (MW = 343,700, MWD = 3.674).

#### EXAMPLE 17

##### Polymerization - Compound A

The polymerization was performed in a stirred 100 ml stainless steel autoclave which was equipped to perform polymerizations at pressures up to 40,000 psi and temperatures up to 300°C. The reactor was purged with nitrogen and heated to 160°C. Compound A and alumoxane solutions were prepared in separate vials. A stock solution was prepared by dissolving

-54-

26 mg of compound A in 100 ml of toluene. The compound A solution was prepared by diluting 0.5 ml of the stock solution with 5.0 ml of toluene. The alumoxane solution consisted of 2.0 ml of a 4% MAO solution added to 5.0 ml of toluene. The compound A solution was added to the alumoxane solution, then 0.43 ml of the mixed solutions were transferred by nitrogen pressure into a constant-volume injection tube. The autoclave was pressurized with ethylene to 1784 bar and was stirred at 1500 rpm. The mixed solutions were injected into the stirred reactor with excess pressure, at which time a temperature rise of 4°C was observed. The temperature and pressure were recorded continuously for 120 seconds, at which time the contents of the autoclave were rapidly vented into a receiving vessel. The reactor was washed with xylene to recover any additional polymer remaining. These washings were combined with the polymer released when the autoclave was vented to yield 0.7 g of polyethylene (MW = 245,500, MWD = 2.257).

#### EXAMPLE 18

##### Polymerization - Compound B

Using the general procedure described in Example 1, 400 ml of toluene, 5.0 ml of 1.0 M MAO and 0.278 mg of compound B (0.2 ml of a 13.9 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated to 80°C and the ethylene (60 psi) was introduced into the system. The polymerization reaction was limited to 10



-55-

minutes. The reaction was ceased by rapidly cooling and venting the system. The solvent was evaporated off the polymer by a stream of nitrogen. Polyethylene was recovered (9.6 g, MW = 241,200, MWD = 2.628).

#### EXAMPLE 19

##### Polymerization - Compound C

Using the general procedures described in Example 1, 300 ml of toluene, 4.0 ml of 1.0 M MAO and 0.46 mg of compound C (0.4 ml of a 11.5 mg in 10 ml of toluene solution) was added to the reactor. The reactor was heated to 80°C and the ethylene (60 psi) was introduced into the system. The polymerization reaction was limited to 30 minutes. The reaction was ceased by rapidly cooling and venting the system. The solvent was evaporated off the polymer by a stream of nitrogen. Polyethylene was recovered (1.7 g, MW = 278,400, MWD = 2.142).

#### EXAMPLE 20

##### Polymerization - Compound D

Using the general procedure described in Example 1, 400 ml of toluene, 5.0 ml of 1.0 M MAO and 0.278 mg of compound D (0.2 ml of a 13.9 mg in 10 ml of toluene solution) was added to the reactor. The reactor was heated to 80°C and ethylene (60 psi) was introduced into the system. The polymerization reaction was limited to 30 minutes. The reaction was ceased by rapidly cooling and venting the system. The solvent was evaporated off the polymer by a

-56-

stream of nitrogen. Polyethylene was recovered (1.9 g, MW = 229,700, MWD = 2.618).

#### EXAMPLE 21

##### Polymerization - Compound E

5           Using the general procedure described in  
Example 1, 300 ml of hexane, 9.0 ml of 1.0 M MAO and  
0.24 mg of compound E (0.2 ml of a 12.0 mg in 10 ml  
of toluene solution) was added to the reactor. The  
10       reactor was heated to 80°C and ethylene (60 psi) was  
introduced into the system. The polymerization  
reaction was limited to 30 minutes. The reaction was  
ceased by rapidly cooling and venting the system.  
The solvent was evaporated off the polymer by a  
stream of nitrogen. Polyethylene was recovered (2.2  
15       g, MW = 258,200, MWD = 2.348).

#### EXAMPLE 22

##### Polymerization - Compound E

          The polymerization was carried out as in  
Example 1 except with the following reactor  
20       conditions: 200 ml of toluene, 100 ml of 1-butene,  
9.0 ml of 1.0 M MAO and 2.4 mg of compound E (2.0 ml  
of a 12.0 mg in 10 ml of toluene solution) at 50°C.  
The reactor was pressurized with ethylene (65 psi),  
and the reaction was allowed to run for 30 minutes,  
25       followed by rapidly cooling and venting the system.  
After evaporation of the solvent, 1.8 g of an  
ethylene-1-butene copolymer was recovered (MW =  
323,600, MWD = 2.463, 33.5 SCB/1000C by IR).

-57-

EXAMPLE 23Polymerization - Compound F

5 The polymerization was carried out as in Example 1 with the following reactor conditions: 400 ml of toluene, 5.0 ml of 1.0 M MAO, 0.242 mg of compound F (0.2 ml of a 12.1 mg in 10 ml of toluene solution), 80°C, 60 psi ethylene, 30 minutes. The run provided 5.3 g of polyethylene (MW = 319,900, MWD = 2.477).

EXAMPLE 24

10

Polymerization - Compound F

15 The polymerization was carried out as in Example 1 with the following reactor conditions: 150 ml of toluene, 100 ml of 1-butene, 9.0 ml of 1.0 M MAO, 2.42 mg of compound F (2.0 ml of a 12.1 mg in 10 ml of toluene solution), 50°C, 65 psi ethylene, 30 minutes. The run provided 3.5 g of an ethylene-1-butene copolymer (MW = 251,300, MWD = 3.341, 33.3 SCB/1000C by IR).

20

EXAMPLE 25Polymerization - Compound G

25 The polymerization was carried out as in Example 1 with the following reactor conditions: 400 ml of toluene, 5.0 ml of 1.0 M MAO, 0.29 mg of compound G (0.2 ml of a 14.5 mg in 10 ml of toluene solution), 80°C, 60 psi ethylene, 30 minutes. The

-58-

run provided 3.5 g of polyethylene (MW = 237,300, MWD = 2.549).

#### EXAMPLE 26

##### Polymerization - Compound G

5           The polymerization was carried out as in  
Example 1 with the following reactor conditions: 150  
ml of toluene, 100 ml of 1-butene, 7.0 ml of 1.0 M  
MAO, 2.9 mg of compound G (2.0 ml of a 14.5 mg in 10  
10          ml of toluene solution), 50°C, 65 psi ethylene, 30  
minutes. The run provided 7.0 g of an ethylene-1-  
butene copolymer (MW = 425,000, MWD = 2.816, 27.1  
SCB/1000C by IR).

#### EXAMPLE 27

##### Polymerization - Compound H

15           The polymerization was carried out as in  
Example 1 with the following reactor conditions:  
400 ml of toluene, 5.0 ml of 1.0 M MAO, 0.266 mg of  
compound H (0.2 ml of a 13.3 mg in 10 ml of toluene  
solution), 80°C, 60 psi ethylene, 30 minutes. The  
20          run provided 11.1 g of polyethylene (MW = 299,800,  
MWD = 2.569).

#### EXAMPLE 28

##### Polymerization - Compound H

25           The polymerization was carried out as in  
Example 1 with the following reactor conditions: 150  
ml of toluene, 100 ml of 1-butene, 7.0 ml of 1.0 M  
MAO, 2.66 mg of compound H (2.0 ml of a 13.3 mg in  
10 ml of toluene solution), 50°C, 65 psi ethylene,  
30 minutes. The run provided 15.4 g of an

-59-

ethylene-1-butene copolymer (MW = 286,600, MWD = 2.980, 45.4 SCB/100OC by IR).

EXAMPLE 29

Polymerization - Compound I

5       The polymerization was carried out as in  
Example 1 with the following reactor conditions: 400  
ml of toluene, 5.0 ml of 1.0 MAO, and 0.34 mg of  
compound I (0.2 ml of a 17.0 mg in 10 ml of toluene  
10       solution). The reactor was heated to 80°C, the  
ethylene was introduced (60 psi), and the reaction  
was allowed to run for 30 minutes, followed by  
rapidly cooling and venting the system. After  
evaporation of the solvent, 0.9 g of polyethylene  
was recovered (MW = 377,000, MWD = 1.996).

15       EXAMPLE 30

Polymerization - Compound J

      The polymerization was carried out as in  
Example 1 with the following reactor conditions: 400  
ml of toluene, 5.0 ml of 1.0 M MAO, 0.318 mg of  
20       compound J (0.2 ml of a 15.9 mg in 10 ml of toluene  
solution), 80°C, 60 psi ethylene, 30 minutes. The  
run provided 8.6 g of polyethylene (MW = 321,000,  
MWD = 2.803).

EXAMPLE 31

25       Polymerization - Compound J

      The polymerization was carried out as in  
Example 1 with the following reactor conditions: 150  
ml of toluene, 100 ml of 1-butene, 7.0 ml of 1.0 M  
MAO, 3.18 mg of compound J (2.0 ml of a 15.9 mg in  
30       10 ml of toluene solution), 50°C, 65 psi ethylene,

-60-

30 minutes. The run provided 11.2 g of an ethylene-1-butene copolymer (MW = 224,800, MWD = 2.512, 49.6 SCB/100OC by IR technique, 55.4 SCB/100OC by NMR).

5

EXAMPLE 32Polymerization - Compound K

The polymerization was carried out as in Example 1 with the following reactor conditions: 300 ml of toluene, 5.0 ml of 1.0 M MAO, 0.272 mg of compound K (0.2 ml of a 13.6 mg in 10 ml of toluene solution), 80°C, 60 psi ethylene, 30 minutes. The run provided 26.6 g of polyethylene (MW = 187,300, MWD = 2.401).

10

EXAMPLE 33Polymerization - Compound K

The polymerization was carried out as in Example 1 with the following reactor conditions: 150 ml of toluene, 100 ml of 1-butene, 7.0 ml of 1.0 M MAO, 2.72 mg of compound K (2.0 ml of a 13.6 mg in 10 ml of toluene solution), 50°C, 65 psi ethylene, 30 minutes. The run provided 3.9 g of an ethylene-1-butene copolymer (MW = 207,600, MWD = 2.394, 33.9 SCB/100OC by IR).

20

EXAMPLE 34Polymerization - Compound L

The polymerization was carried out as in Example 1 with the following reactor conditions: 400 ml of toluene, 5.0 ml of 1.0 M MAO, 0.322 mg of compound L (0.2 ml of a 16.1 mg in 10 ml of toluene solution), 80°C, 60 psi ethylene, 30 minutes. The

30

-61-

run provided 15.5 g of polyethylene (MW = 174,300, MWD = 2.193).

#### EXAMPLE 35

##### Polymerization - Compound A

5       The polymerization was carried out as in  
Example 1 with the following reactor contents: 250  
ml of toluene, 150 ml of 1-hexene, 7.0 ml of 1.0 M  
MAO and 2.3 mg of compound A (2.0 ml of a 11.5 mg in  
10 ml of toluene solution) at 50°C. The reactor was  
10       pressurized with ethylene (65 psi), and the reaction  
was allowed to run for 30 minutes, followed by  
rapidly cooling and venting the system. After  
evaporation of the solvent, 26.5 g of an ethylene-1-  
hexane copolymer was recovered (MW = 222,800, MWD =  
15       3.373, 39.1 SCB/1000C by IR).

#### EXAMPLE 36

##### Polymerization - Compound A

20       The polymerization was carried out as in  
Example 1 with the following reactor contents: 300  
ml of toluene, 100 ml of 1-octene, 7.0 ml of 1.0 M  
MAO and 2.3 mg of compound A (2.0 ml of a 11.5 mg in  
10 ml of toluene solution) at 50°C. The reactor was  
pressurized with ethylene (65 psi), and the reaction  
was allowed to run for 30 minutes, followed by  
25       rapidly cooling and venting the system. After  
evaporation of the solvent, 19.7 g of an ethylene-1-  
octene copolymer was recovered (MW = 548,600, MWD =  
3.007, 16.5 SCB/1000C by <sup>13</sup>C NMR).

-62-

EXAMPLE 37Polymerization - Compound A

The polymerization was carried out as in Example 1 with the following reactor conditions: 300 ml of toluene, 100 ml of 4-methyl-1-pentene, 7.0 ml of 1.0 M MAO and 2.3 mg of compound A (2.0 ml of a 11.5 mg in 10 ml of toluene solution) at 50°C. The reactor was pressurized with ethylene (65 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 15.1 g of an ethylene-4-methyl-1-pentene copolymer was recovered (MW = 611,800, MWD = 1.683, 1.8 mole % determined by  $^{13}\text{C}$  NMR).

EXAMPLE 38Polymerization - Compound A

The polymerization was carried out as in Example 1 with the following reactor conditions: 300 ml of toluene, 100 ml of a 2.2 M norbornene in toluene solution, 7.0 ml of 1.0 M MAO and 2.3 mg of compound A (2.0 ml of a 11.5 mg in 10 ml of toluene solution) at 50°C. The reactor was pressurized with ethylene (65 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 12.3 g of an ethylene-norbornene copolymer was recovered (MW = 812,600, MWD = 1.711, 0.3 mole % determined by  $^{13}\text{C}$  NMR).



-63-

EXAMPLE 39Polymerization - Compound A

The polymerization was carried out as in Example 1 with the following reactor contents: 300 ml of toluene, 100 ml of cis-1,4-hexadiene, 7.0 ml of 1.0 M MAO and 2.3 mg of compound A (2.0 ml of a 11.5 mg in 10 ml of toluene solution) at 50°C. The reactor was pressurized with ethylene (65 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 13.6 g of an ethylene-cis-1,4-hexadiene copolymer was recovered (MW = 163,400, MWD = 2.388, 2.2 mole % determined <sup>13</sup>C NMR).

EXAMPLE 40Polymerization - Compound AT

The polymerization run was performed in a 12-liter autoclave reactor equipped with a paddle stirrer, an external water jacket for temperature control, a regulated supply of dry nitrogen, ethylene, propylene, 1-butene and hexane, and a septum inlet for introduction of other solvents or comonomers, transition metal compound and alumoxane solutions. The reactor was dried and degassed thoroughly prior to use. A typical run consisted of injecting 400 ml of toluene, 5 ml of 1.0 M MAO, 0.206 mg compound AT (0.2 ml of a 10.3 mg in 10 ml of toluene solution) into the reactor. The reactor was then heated to 80°C and the ethylene (60 psi) was introduced into the system. The polymerization reaction was limited to 30 minutes.

-64-

The reaction was ceased by rapidly cooling and venting the system. The solvent was evaporated off of the polymer by a stream of nitrogen. Polyethylene was recovered (11.8 g, MW = 279,700, MWD = 2.676).

5

EXAMPLE 41Polymerization - Compound AT

Using the same reactor design and general procedure as described in Example 40, 400 ml of toluene, 5.0 ml of 1.0 M MAO, and 0.2 ml of a preactivated compound AT solution (10.3 mg of compound AT dissolved in 9.5 ml of toluene and 0.5 ml of 1.0 M MAO) were added to the reactor. The reactor was heated to 80°C, the ethylene was introduced (60 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the solvent, 14.5 g of polyethylene was recovered (MW = 406,100, MWD = 2.486).

10

15

EXAMPLE 42Polymerization - Compound AT

Using the same reactor design and general procedure described in Example 40, 300 ml of toluene, 100 ml of 1-hexene, 7.0 ml of 1.0 M MAO, and 1.03 mg of compound AT (1.0 ml of 10.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 48.6 g of an

20

25

-65-

ethylene-1-hexene copolymer was recovered (MW = 98,500, MWD = 1.745, 117 SCB/1000C by  $^{13}\text{C}$  NMR).

#### EXAMPLE 43

##### Polymerization - Compound AT

5        Using the same reactor design and general procedure described in Example 40, 375 ml of toluene, 25 ml of 1-hexene, 7.0 ml of 1.0 M MAO, and 1.03 mg of compound AT (1.0 ml of a 10.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was  
10       heated at 80°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 29.2 g of an  
15       ethylene-1-hexene copolymer was recovered (MW = 129,800, MWD = 2.557, 53.0 SCB/1000C by  $^{13}\text{C}$  NMR).

#### EXAMPLE 44

##### Polymerization - Compound AT

20       Using the same reactor design and general procedure described in Example 40, 375 ml of toluene, 25 ml of 1-hexene, 7.0 ml of 1.0 M MAO, and 1.03 mg of compound AT (1.0 ml of 10.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was  
25       heated at 50°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 15.0 g of an  
ethylene-1-hexene copolymer was recovered (MW = 310,000, MWD = 2.579, 47.2 SCB/1000C by  $^{13}\text{C}$  NMR).

-66-

EXAMPLE 45Polymerization - Compound AT

Using the same reactor design and general procedure described in Example 40, 300 ml of toluene, 100 ml of propylene, 7.0 ml of 1.0 M MAO, and 2.06 mg of compound AT (2.0 ml of a 10.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 46.0 g of an ethylene-propylene copolymer was recovered (MW = 110,200, MWD = 5.489, 20 wt% ethylene by IR).

EXAMPLE 46Polymerization - Compound AT

Using the same reactor design and general procedure described in Example 40, 300 ml of toluene, 100 ml of 1-butene, 7.0 ml of 1.0 M MAO, and 1.03 mg of compound AT (1.0 ml of a 10.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 35.1 g of an ethylene-1-butene copolymer was recovered (MW = 94,400, MWD = 2.405, 165 SCB/1000C by <sup>13</sup>C NMR).

-67-

EXAMPLE 47Polymerization - Compound AT

Using the same reactor design and general procedure described in Example 40, 300 ml of toluene, 100 ml of 1-octene, 7.0 ml of 1.0 M MAO, and 1.04 mg of compound AT (1.0 ml of a 10.4 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (65 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 30.6 g of an ethylene-1-octene copolymer was recovered (MW = 73,100, MWD = 2.552, 77.7 SCB/1000C by <sup>13</sup>C NMR).

EXAMPLE 48Polymerization - Compound BT

Using the same reactor design and general procedure described in Example 40, 400 ml of toluene, 5.0 ml of 1.0 M MAO, and 0.248 mg of compound BT (0.2 ml of a 12.4 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (60 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 3.8 g of polyethylene was recovered (MW = 451,400, MWD = 3.692).

EXAMPLE 49Polymerization - Compound CT

Using the same reactor design and general procedure described in Example 40, 400 ml of toluene, 5.0 ml of 1.0 M MAO, and 0.234 mg of compound CT (0.2

-68-

ml of a 11.7 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (60 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 2.7 g of polyethylene was recovered (MW = 529,100, MWD = 3.665).

#### EXAMPLE 50

##### Polymerization - Compound DT

Using the same reactor design and general procedure described in Example 40, 400 ml of toluene, 5.0 ml of 1.0 M MAO, and 0.28 mg of compound DT (0.2 ml of a 14.0 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, the ethylene was introduced (60 psi), and the reaction was allowed to run for 10 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 9.0 g of polyethylene was recovered (MW = 427,800, MWD = 3.306).

#### EXAMPLE 51

##### Polymerization - Compound DT

Using the same reactor design and general procedure described in Example 40, 300 ml of toluene, 100 ml propylene, 7.0 ml of 1.0 M MAO, and 1.4 mg of compound DT (1.0 ml of a 14.0 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 30°C and the reaction was allowed to run for 1 hour, followed by rapidly cooling and venting the system. After evaporation of the toluene, 15 g of

-69-

amorphous polypropylene was recovered (MW = 18,600, MWD = 1.657).

#### EXAMPLE 52

##### Polymerization - Compound ET

5        Using the same reactor design and general  
procedure described in Example 40, 300 ml of toluene,  
100 ml 1-hexene, 70 ml of 1.0 M MAO, and 1.0 mg of  
compound ET (1.0 ml of a 10.0 mg in 10 ml of toluene  
10        solution) were added to the reactor. The reactor was  
heated at 80°C and the ethylene was introduced (65  
psi). During the polymerization, the reactor  
temperature increased by 20°C. After 10 minutes, the  
reactor was rapidly cooled and vented. After  
15        evaporation of the toluene, 106 g of an ethylene-1-  
hexene copolymer was recovered (MW = 17,900, MWD =  
2.275, 39.1 SCB/1000C by NMR).

#### EXAMPLE 53

##### Polymerization - Compound AT

20        The polymerization was performed in a stirred 100  
ml stainless steel autoclave which was equipped to  
perform polymerizations at temperatures up to 300°C  
and pressures up to 2500 bar. The reactor was  
evacuated, purged with nitrogen, purged with ethylene  
and heated to 200°C. 1-hexene (75 ml) was added to  
25        the reactor under ethylene pressure. A stock solution  
of compound AT was prepared by dissolving 6.5 mg of  
compound AT in 12.5 ml of toluene. The test solution  
was prepared by adding 1.0 ml of the compound AT stock  
solution to 1.9 ml of 1.0 M MAO solution, followed by  
30        7.1 ml of toluene. The test solution (0.43 ml) was

-70-

transferred by nitrogen pressure into a constant-volume injection tube. The autoclave was pressurized with ethylene to 1748 bar and was stirred at 1800 rpm. The test solution was injected into the autoclave with excess pressure, at which time a temperature rise of 16°C was observed. The temperature and pressure were recorded continuously for 120 seconds, at which time the contents of the autoclave were rapidly vented into a receiving vessel. The reactor was washed with xylene to recover any polymer remaining within. These washings were combined with the polymer released when the reactor was vented. Precipitation of the polymer from the mixture by addition of acetone yielded 2.7 g of polymer (MW = 64,000, MWD = 3.16, 14.7 SCB/1000C by IR).

#### EXAMPLE 54

##### Polymerization - Compound AT

For this Example a stirred 1 L steel autoclave reaction vessel which was equipped to perform continuous Ziegler polymerization reactions at pressures to 2500 bar and temperatures up to 300°C was used. The reaction system was supplied with a thermocouple and pressure transducer to measure temperature and pressure continuously, and with means to supply continuously purified compressed ethylene and 1-butene (or propylene). Equipment for continuously introducing a measured flow of catalysts solution, and equipment for rapidly venting and quenching the reaction, and of collecting the polymer product were also a part of the reaction system. The



-71-

polymerization was performed with a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent. The temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 0.888 g of solid compound AT with 0.67 L of a 30 wt% methylalumoxane solution in 4.3 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.56 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer products was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 50,200, a molecular weight distribution of 2.36 and 60.1 SCB/1000C as measured by <sup>13</sup>C NMR.

#### 20 EXAMPLE 55

##### Polymerization - Compound AT

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to propylene of 2.6 without the addition of a solvent. The temperature of a cleaned reactor containing ethylene and propylene was equilibrated at the desired reaction temperature of 140°C. The catalyst solution was prepared by mixing 0.779 g of solid compound AT with 0.5 L of a 30 wt% methylalumoxane solution in 24.5 L of toluene in an inert atmosphere. This

-72-

catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.9 L/hr which resulted in a temperature of 140°C in the reactor. During this run, ethylene and propylene were  
5 pressured into the autoclave at a total pressure of 2200 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 2.3 kg/hr of an ethylene-propylene copolymer which had a weight average molecular weight of 102,700, a molecular  
10 weight distribution of 2.208 and a density of 0.863 g/cc.

#### EXAMPLE 56

##### Polymerization - Compound FT

Using the same reactor design as described in  
15 Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent. The temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was  
20 prepared by mixing 0.859 g of solid FT with 30 wt% methylalumoxane solution and toluene such that the catalyst concentration was 0.162 g/L with an Al/M molar ratio of 1200. The preparation was done under an inert atmosphere. This catalyst solution was  
25 continuously fed by a high pressure pump into the reactor at a rate of 1.15 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300. The reactor  
30 contents were stirred at 1000 rpm. The yield of

-73-

polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 61,400, a molecular weight distribution of 2.607 and 104.8 SCB/1000C by  $^{13}\text{C}$  NMR.

5

Example 57Polymerization - Compound GT

Using the same reactor design and general procedure as described in Example 40, 300 ml of toluene, 100 ml of 1-hexene, 7.0 ml of 1.0 M MAO, and 1.23 mg of compound GT (1.0 ml of a 12.3 mg in 10 ml of toluene solution) were added to the reactor. The reactor was heated at 80°C, and ethylene was introduced (65 psi), and the reaction was allowed to run for 30 minutes, followed by rapidly cooling and venting the system. After evaporation of the toluene, 47.2 g of an ethylene-1-hexene copolymer was recovered (MW = 313,000, MWD = 3.497, 41.0 SCB/1000C by  $^{13}\text{C}$  NMR.

10  
15EXAMPLE 58Polymerization - Compound AT

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 170°C. The catalyst solution was prepared by mixing 0.925 g of solid compound AT with 2 L of a 10 wt% methylalumoxane solution in 8L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump

20  
25  
30

-74-

into the reactor at a rate of 0.28 L/hr which resulted in a temperature of 170°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.7 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 69,500, a molecular weight distribution of 2.049 and 35.7 SCB/1000C by  $^{13}\text{C}$  NMR.

#### EXAMPLE 59

##### Polymerization - Compound BT

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 0.995 g of solid compound BT with 30 wt% methylalumoxane solution and toluene such that the catalyst concentration was 0.187 g/L and the Al/M molar ratio was 1300. The preparation was done under an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 1.0 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular

-75-

weight of 65,000, a molecular weight distribution of 2.623 and 55.5 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 60

##### Polymerization - Compound H

5           Using the same reactor design as described in  
Example 54, and using a molar ratio of ethylene to 1-  
butene of 1.6 without the addition of a solvent, the  
temperature of the cleaned reactor containing ethylene  
and 1-butene was equilibrated at the desired reaction  
10           temperature of 180°C. The catalyst solution was  
prepared by mixing 1.94 g of solid compound H with 2.0  
L of a 10 wt% methylalumoxane solution in 3L of  
toluene in an inert atmosphere. This catalyst  
solution was continuously fed by a high pressure pump  
15           into the reactor at a rate of 1.5 L/hr which resulted  
in a temperature of 180°C in the reactor. During  
this run, ethylene and 1-butene were pressured into  
the autoclave at a total pressure of 1300 bar. The  
reactor contents were stirred at 1000 rpm. The yield  
20           of polymer product was 3.9 kg/hr of an ethylene-1-  
butene copolymer which had a weight average molecular  
weight of 31,900 and 46.5 SCB/1000C as measured by  $^{13}\text{C}$   
NMR.

#### EXAMPLE 61

##### Polymerization - Compound I

25           Using the same reactor design as described in  
Example 54, and using a molar ratio of ethylene to 1-  
butene of 1.6 without the addition of a solvent, the  
temperature of the cleaned reactor containing ethylene  
and 1-butene was equilibrated at the desired reaction  
30

-76-

temperature of 180°C. The catalyst solution was prepared by mixing 1.92 g of solid compound I with 2.0 L of a 10 wt% methylalumoxane solution in 3 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.67 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 40,800, a molecular weight distribution of 2.009 and 36.9 SCB/1000C as measured by <sup>13</sup>C NMR.

15

EXAMPLE 62Polymerization - Compound K

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.80 g of solid compound K with 2.0 L of a 10 wt% methylalumoxane solution in 3L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 1.7 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The

-77-

reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 51,700, a molecular weight distribution of 1.532 and 30.1 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 63

##### Polymerization - Compound L

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.95 g of solid compound L with 2.0 L of a 10 wt% methylalumoxane solution in 3 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 1.2 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 38,800, a molecular weight distribution of 1.985 and 39.3 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 64

##### Polymerization - Compound HT

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-

-78-

butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 2.01 g of solid compound HT with 30 wt% methylalumoxane solution and toluene such that the catalyst concentration was 0.354 g/L and the Al/M molar ratio was 400. The preparation was done under an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 1.15 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 61,700, a molecular weight distribution of 2.896 and 62.9 SCB/1000C as measured by <sup>13</sup>C NMR.

#### EXAMPLE 65

##### Polymerization - Compound F

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.31 g of solid compound F with 2.0 L of a 10 wt% methylalumoxane solution in 3 L of toluene in an inert atmosphere. This catalyst



-79-

solution was continuously fed by a high pressure pump into the reactor at a rate of 0.56 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the  
5     autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 43,400, a molecular weight distribution of  
10     2.001 and 40.1 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

EXAMPLE 66

Polymerization - Compound G

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the  
15     temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.53 g of solid compound G with 0.5  
20     L of a 30 wt% methylalumoxane solution in 4.5 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.58 L/hr which resulted in a temperature of 180°C in the reactor. During this  
25     run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular

-80-

weight of 47,400, a molecular weight distribution of 2.198 and 37.6 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 67

##### Polymerization - Compound IT

5           Using the same reactor design as described in  
Example 54, and using a molar ratio of ethylene to 1-  
butene of 1.6 without the addition of a solvent, the  
temperature of the cleaned reactor containing ethylene  
and 1-butene was equilibrated at the desired reaction  
10   temperature of 180°C. The catalyst solution was  
prepared by mixing 1.94 g of solid compound IT with 30  
wt% methylalumoxane solution and toluene such that the  
catalyst concentration was 0.388 g/L and the Al/M  
molar ratio was 600. The preparation was done under  
15   an inert atmosphere. This catalyst solution was  
continuously fed by a high pressure pump into the  
reactor at a rate of 0.42 L/hr which resulted in a  
temperature of 180°C in the reactor. During this run,  
ethylene and 1-butene were pressured into the  
20   autoclave at a total pressure of 1300 bar. The reactor  
contents were stirred at 1000 rpm. The yield of  
polymer product was 3.9 kg/hr of an ethylene-1-butene  
copolymer which had a weight average molecular weight  
of 50,800, a molecular weight distribution of 2.467  
25   and 69 SCB/1000C as measured by  $^1\text{H}$  NMR.

#### EXAMPLE 68

##### Polymerization - Compound A

          Using the same reactor design as described in  
Example 54, and using a molar ratio of ethylene to 1-  
30   butene of 1.6 without the addition of a solvent, the

-81-

temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.95 g of solid compound A with  
5 0.67 L of a 30 wt% methylalumoxane solution in 4.3 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.4 L/hr which resulted in a temperature of 180°C in the reactor. During this  
10 run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer products was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 71,100, a molecular weight distribution of  
15 1.801 and 12.4 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 69

##### Polymerization - Compound B

Using the same reactor design as described in  
20 Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.97 g of solid compound B with  
25 0.67 L of a 30 wt% methylalumoxane solution in 4.3 L of toluene in an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.35 L/hr which resulted  
30 in a temperature of 180°C in the reactor. During this

-82-

run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which has a weight average molecular weight of 47,300, and a molecular weight distribution of 2.056 and 34.1 SCB/1000C as measured by  $^{13}\text{C}$  NMR.

#### EXAMPLE 70

##### Polymerization - Compound JT

Using the same reactor design as described in Example 54, and using a molar ratio of ethylene to 1-butene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 1.78 g of solid compound JT with 30 wt% methylalumoxane solution and toluene such that the catalyst concentration was 0.318 g/L and the Al/M molar ratio was 1400. The preparation was done under an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.55 L/hr which resulted in a temperature of 180°C in the reactor. During thus run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm. The yield of polymer product was 3.9 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 72,600, a molecular weight distribution of 2.385 and 110 SCB/1000C as measured by  $^1\text{H}$  NMR.

-83-

Table 2 summarizes the polymerization conditions employed and the properties obtained in the product polymers as set forth in Examples 1-39 above.

TABLE 2

EXP. NO.	DILUENT		TRANSITION METAL COMPOUND (THC)		ALUOXANE		mmole MAO:THC (X10 <sup>3</sup> )	MONOMER	COMONOMER	RXN. TEMP. °C	RXN. TIME HR.	YIELD %	MW	MWD	SCB/ 1000C		CAT. ACTIVITY G. POLYMER/MOLE THC-HOUR
	Type	ml	Type	mmole	Type	mmole									MNR	IR	
4	Hexane	300	A	5.588x10 <sup>-4</sup>	MAO	9	16.11	ethylene-60 psi		80	0.5	5.4	212,600	2.849			1.933x10 <sup>4</sup>
1	Toluene	400	A	5.588x10 <sup>-4</sup>	MAO	9	16.11	ethylene-60 psi		80	0.5	9.2	257,200	2.275			3.293x10 <sup>4</sup>
2	Toluene	300	A	2.794x10 <sup>-4</sup>	MAO	4.5	16.11	ethylene-60 psi		80	0.5	3.8	359,800	2.425			2.720x10 <sup>4</sup>
3	Toluene	300	A	2.794x10 <sup>-4</sup>	MAO	4.5	16.11	ethylene-60 psi		40	0.5	2.4	635,000	3.445			1.718x10 <sup>4</sup>
16	Toluene	400	A	5.588x10 <sup>-4</sup>	MAO	5	8.95	ethylene-400 psi		80	0.5	19.4	343,700	3.674			6.943x10 <sup>4</sup>
<hr/>																	
12	Toluene	400	A <sup>a</sup>	5.588x10 <sup>-4</sup>	MAO	5.02	8.98	ethylene-60 psi		80	0.5	3.4	285,000	2.808			1.217x10 <sup>4</sup>
13	Toluene	400	A <sup>a, b</sup>	5.588x10 <sup>-4</sup>	MAO	5.02	8.98	ethylene-60 psi		80	0.5	2.0	260,700	2.738			7.158x10 <sup>3</sup>
14	Toluene	400	A <sup>a</sup>	5.588x10 <sup>-4</sup>	MAO	0.26	0.47	ethylene-60 psi		80	0.5	1.1	479,600	3.130			3.937x10 <sup>3</sup>
15	Toluene	400	A <sup>a</sup>	5.588x10 <sup>-4</sup>	MAO	0.1	0.018	ethylene-60 psi		80	0.5	1.6	458,800	2.037			5.727x10 <sup>2</sup>
<hr/>																	
18	Toluene	400	B	5.573x10 <sup>-4</sup>	MAO	5	8.97	ethylene-60 psi		80	0.17	9.6	241,200	2.628			1.034x10 <sup>3</sup>
19	Toluene	300	C	1.118x10 <sup>-3</sup>	MAO	4	3.58	ethylene-60 psi		80	0.5	1.7	278,400	2.142			3.041x10 <sup>3</sup>
20	Toluene	400	D	5.573x10 <sup>-4</sup>	MAO	5	8.97	ethylene-60 psi		80	0.5	1.9	229,700	2.618			6.819x10 <sup>3</sup>

SUBSTITUTE SHEET

TABLE 2

EXP. NO.	DILUENT		TRANSITION METAL COMPOUND (THC)		ALUMOXANE		MAO:THC (X10 <sup>3</sup> )	MONOMER	COMONOMER	RXN. TEMP. °C	RXN. TIME HR.	YIELD g.	MW	MWD	SCB/1000C		CAT. ACTIVITY G. POLYMER/Hg. THC-HOUR
	Type	ml	Type	mole	Type	mole									HR	IR	
21	Hexane	300	E	5.61x10 <sup>-4</sup>	MAO	9	16.04	ethylene-60 psi		80	0.5	2.2	258,200	2.348			7.843x10 <sup>3</sup>
23	Toluene	400	F	4.79x10 <sup>-4</sup>	MAO	5	10.44	ethylene-60 psi		80	0.5	5.3	319,900	2.477			2.213x10 <sup>4</sup>
25	Toluene	400	G	5.22x10 <sup>-4</sup>	MAO	5	9.58	ethylene-60 psi		80	0.5	3.5	237,300	2.549			1.341x10 <sup>4</sup>
27	Toluene	400	H	5.62x10 <sup>-4</sup>	MAO	5	8.90	ethylene-60 psi		80	0.5	11.1	299,800	2.569			3.950x10 <sup>4</sup>
29	Toluene	400	I	5.57x10 <sup>-4</sup>	MAO	5	8.98	ethylene-60 psi		80	0.5	0.9	377,000	1.996			3.232x10 <sup>3</sup>
30	Toluene	400	J	5.59x10 <sup>-4</sup>	MAO	5	8.94	ethylene-60 psi		80	0.5	8.6	321,000	2.803			3.077x10 <sup>4</sup>
32	Toluene	300	K	5.06x10 <sup>-4</sup>	MAO	5	9.87	ethylene-60 psi		80	0.5	26.6	187,300	2.401			1.051x10 <sup>5</sup>
34	Toluene	400	L	5.60x10 <sup>-4</sup>	MAO	5	8.93	ethylene-60 psi		80	0.5	15.5	174,300	2.193			5.536x10 <sup>4</sup>
5	Toluene	300	A	1.118x10 <sup>-3</sup>	MAO	9	8.05	ethylene-60 psi	propylene-200 ml	80	0.5	13.3	24,900	2.027		73.5	2.379x10 <sup>4</sup>
6	Toluene	200	A	2.235x10 <sup>-3</sup>	MAO	9	4.03	ethylene-60 psi	propylene-200 ml	50	0.5	6.0	83,100	2.370		75.7	5.369x10 <sup>3</sup>
7	Toluene	150	A	5.588x10 <sup>-3</sup>	MAO	9	1.61	ethylene-65 psi	1-butene-100 ml	50	0.5	25.4	184,500	3.424		23.5	9.091x10 <sup>3</sup>
8	Toluene	100	A	5.588x10 <sup>-3</sup>	MAO	9	1.61	ethylene-65 psi	1-butene-150 ml	50	0.5	30.2	143,400	3.097		30.8	1.081x10 <sup>4</sup>
9	Toluene	200	A	5.588x10 <sup>-3</sup>	MAO	8	1.43	ethylene-65 psi	1-butene-50 ml	50	0.5	24.9	163,200	3.290		23.3	8.912x10 <sup>3</sup>
10	Hexane	200	A	5.588x10 <sup>-3</sup>	MAO	8	1.43	ethylene-65 psi	1-butene-50 ml	50	0.5	19.5	150,600	3.510		12.1	6.979x10 <sup>3</sup>
11	Hexane	150	A	5.588x10 <sup>-3</sup>	MAO	8	1.43	ethylene-65 psi	1-butene-100 ml	50	0.5	16.0	116,200	3.158		19.2	5.727x10 <sup>3</sup>

TABLE 2

EXP. NO.	DILUENT		TRANSITION METAL COMPOUND (TMC)		ALUMOXANE		mole MAO:TMC (X10 <sup>-3</sup> )	MONOMER	COMONOMER	RXN. TEMP. °C	RXN. TIME HR.	YIELD %	MW	MWD	SCB/1000C	CAT. ACTIVITY G. POLYMER/MOLE TMC-HOUR
	Type	ml	Type	mole	Type	mole										
22	Toluene	200	E	5.61x10 <sup>-3</sup>	MAO	9	1.60	ethylene-65 psi	1-butene-100 ml	50	0.5	1.8	323,600	2.463	33.5	6.417x10 <sup>2</sup>
24	Toluene	150	F	4.79x10 <sup>-3</sup>	MAO	9	1.88	ethylene-65 psi	1-butene-100 ml	50	0.5	3.5	251,300	3.341	33.3	1.461x10 <sup>3</sup>
26	Toluene	150	G	5.22x10 <sup>-3</sup>	MAO	7	1.34	ethylene-65 psi	1-butene-100 ml	50	0.5	7.0	425,000	2.816	27.1	2.682x10 <sup>3</sup>
28	Toluene	150	H	5.62x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	15.4	286,600	2.980	45.4	5.480x10 <sup>3</sup>
30	Toluene	150	J	5.59x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	11.2	224,800	2.512	49.6	4.007x10 <sup>3</sup>
32	Toluene	150	K	5.06x10 <sup>-3</sup>	MAO	7	1.38	ethylene-65 psi	1-butene-100 ml	50	0.5	3.9	207,600	2.394	33.9	1.542x10 <sup>3</sup>
35	Toluene	250	A	5.588x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	26.5	222,800	3.373	39.1	9.485x10 <sup>3</sup>
36	Toluene	300	A	5.588x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	19.7	548,600	3.007	16.5	6.979x10 <sup>3</sup>
37	Toluene	300	A	5.588x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	15.1	611,800	1.683	1.8 <sup>c</sup>	5.404x10 <sup>3</sup>
38	Toluene	300	A	5.588x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	12.3	812,600	1.711	0.3 <sup>c</sup>	4.402x10 <sup>3</sup>
39	Toluene	300	A	5.588x10 <sup>-3</sup>	MAO	7	1.25	ethylene-65 psi	1-butene-100 ml	50	0.5	13.6	163,400	2.388	2.2 <sup>c</sup>	4.868x10 <sup>3</sup>

a Compound A was preactivated by dissolving the compound in solvent containing MAO.

b Preincubation of activated compound A was for one day.

c Mole % comonomer.



-87-

Tables A, B, and C summarize the polymerization conditions employed and the properties obtained in the polymer products of Example Nos. 40-50, 52, 54-59, 64, 67 and 70 wherein a titanium species of Group IV B metal component is employed in the catalyst system.

Table D summarizes the condition employed and properties obtained in the polymer products produced by catalyst systems wherein each Group IV B metal is the species of a monocyclopentadienyl compound which is otherwise of identical structure except for the identity of the Group IV B metal itself.

TABLE A

Example Number	Transition Metal Compound (THC) Type	Methylalumoxane (MAO) mmole	mmole MAO/THC ( $\times 10^3$ )	Ethylene Pressure (psi)	Run Temp. °C	Run Time hr.	Yield g	MW	MWD	Cat Activity g poly/mmole THC-HR
41 <sup>a</sup>	AT	$4.79 \times 10^{-4}$	5.01	60	80	0.5	14.5	406,100	2.486	$6.05 \times 10^4$
40	AT	$4.79 \times 10^{-4}$	5	60	80	0.5	11.8	279,700	2.676	$4.93 \times 10^4$
50	DT	$5.59 \times 10^{-4}$	5	60	80	0.166	9.0	427,800	3.306	$9.70 \times 10^4$
48	BT	$5.58 \times 10^{-4}$	5	60	80	0.166	3.6	451,400	3.692	$4.10 \times 10^4$
49	CT	$5.59 \times 10^{-4}$	5	60	80	0.166	2.7	529,100	3.665	$2.91 \times 10^4$

<sup>a</sup> Transition metal compound was preactivated before polymerization by adding it with a quantity of methylalumoxane sufficient to provide a MAO/THC ratio of 20.9.

TABLE 3

Example Number	Transition Metal Compound (THCl) Type	Methylalumoxane (MAO) mmole	mmole MAO/THCl ( $\times 10^3$ )	Ethylene Pressure (psig)	Comonomer Amount	Rxn. Temp. °C	Rxn. Time hr.	Yield g	MW	MWD	SCB/1000g <sup>c</sup>
45	AT	$4.79 \times 10^{-3}$	7	65	Propylene: 100 ml	80	0.166	46.0	110,200	5.489	(Propylene) <sup>b</sup> 80 wt%
46	AT	$2.39 \times 10^{-3}$	7	65	1-Butene: 100 ml	80	0.166	35.1	94,400	2.405	165
44	AT	$2.39 \times 10^{-3}$	7	65	1-Hexene: 25 ml	50	0.166	15.0	310,000	2.579	47.2
43	AT	$2.39 \times 10^{-3}$	7	65	1-Hexene: 25 ml	80	0.166	29.2	129,800	2.557	53.0
42	AT	$2.39 \times 10^{-3}$	7	65	1-Hexene: 100 ml	80	0.166	48.6	98,500	1.745	117
52	ET	$2.76 \times 10^{-3}$	7	65	1-Hexene: 100 ml	80 <sup>d</sup>	0.166	106	17,900	2.275	39.1
57	GT	$2.81 \times 10^{-3}$	7	65	1-Hexene: 100 ml	80	0.5	47.2	313,000	3.497	41.0
47	AT	$2.42 \times 10^{-3}$	7	65	1-Octene: 100 ml	80	0.166	30.6	73,100	2.552	77.7

<sup>b</sup> Determined by IR<sup>c</sup> Determined by <sup>13</sup>C NMR<sup>d</sup> During polymerization the reactor temperature increased by 20-C.

-90-

TABLE C

Example Number	Transition Metal Compound (TMC)	Al/TMC	Catalyst TMC Feed Rate (mmole/hr)	Comonomer (Gmol)	Ethylene/Com Mole Ratio	Rxn. Pressure (bar)	Rxn. Temp. (°C)	Yield (kg/hr)	MW	PCS <sup>a</sup> /1000G	Cat. Activity kg Polymer/mol TMC
53 <sup>e</sup>	AT	1200	1.63	Propylene	2.6	2200	140	2.3	2.208	127.7	1.4
54	AT	1500	0.231	1-Butene	1.6	1300	180	3.9	2.36	60.1	16.9
67	IT	600	0.442	1-Butene	1.6	1300	180	3.9	2.467	69 <sup>d</sup>	8.8
64	IT	400	1.05	1-Butene	1.6	1300	180	3.9	2.896	62.9	3.7
59	IT	1300	0.421	1-Butene	1.6	1300	180	3.9	2.623	55.5	9.3
58	AT	1400	0.060	1-Butene	1.6	1300	170	3.7	2.049	35.7	61.7
56	PT	1200	0.366	1-Butene	1.6	1300	180	3.9	2.607	104.8	8.3
70	JT	1400	0.366	1-Butene	1.6	1300	180	3.9	2.385	110 <sup>d</sup>	10.7

<sup>a</sup> The polymer product had a density of 0.863 g/cc. <sup>13</sup>C NMR.

<sup>d</sup> Excepted where otherwise indicated, determined by <sup>1</sup>H NMR.

<sup>e</sup> Determined by <sup>1</sup>H NMR.

SUBSTITUTE SHEET

-91-

TABLE D

Example Number	Transition Metal Compound (THC)	TH	Catalyst THC Feed Rate mmole/hr	Cat. Activity <sup>a</sup> kg Polymer/ mmol THC	MW	MWD	SCB/1000C	FI
54	AT	Ti	0.23	17.0	50,200	2.360	60.1	10.1
60	H	Zr	1.23	3.2	31,900	12.070	46.6	14.1
61	I	Hf	0.42	9.3	40,800	2.009	36.9	18.4
59	BT	Ti	0.42	9.3	65,000	2.623	55.5	11.2
62	K	Zr	1.25	3.1	51,700	1.532	30.1	23.4
63	L	Hf	0.81	4.8	1.15	1.985	39.3	17.2
64	HT	Ti	1.05	3.7	61,700	2.896	62.9	9.5
65	F	Zr	0.34	11.5	43,400	2.001	40.1	16.8
66	G	Hf	0.34	11.5	47,400	2.198	37.6	18.1
67	IT	Ti	0.44	8.9	50,800	2.467	69	8.4
68	A	Zr	0.38	10.3	71,100	1.801	12.4	59.9
69	B	Hf	0.69	5.7	47,300	2.056	34.1	20.3


<sup>a</sup> Polymer yield was 3.90 kg/hr.

-92-

It may be seen that the requirement for the alumoxane component can be greatly diminished by premixing the catalyst with the alumoxane prior to initiation of the polymerization (see Examples 12 through 15).

By appropriate selection of (1) Group IV B transition metal component for use in the catalyst system; (2) the type and amount of alumoxane used; (3) the polymerization diluent type and volume; (4) reaction temperature; and (5) reaction pressure, one may tailor the product polymer to the weight average molecular weight value desired while still maintaining the molecular weight distribution to a value below about 4.0. The preferred polymerization diluents for practice of the process of the invention are aromatic diluents, such as toluene, or alkanes, such as hexane.

From the above examples it appears that for a catalyst system wherein the group IV B transition metal component is a titanium species of the following structure:



-93-

the nature of the R' group may dramatically influence the catalytic properties of the system. For production of ethylene- $\alpha$ -olefin copolymers of greatest comonomer content, at a selected ethylene to  $\alpha$ -olefin monomer ratio, R' is preferably a non-aromatic substituent, such as an alkyl or cycloalkyl substituent preferably bearing as primary or secondary carbon atom attached to the nitrogen atom.

Further, from the above data, the nature of the Cp ligand structure of a Ti metal component may be seen to influence the properties of the catalyst system. Those Cp ligands which are not too sterically hindered and which contain good electron donor groups, for example the Me<sub>4</sub>C<sub>5</sub> ligand, are preferred.


The resins that are prepared in accordance with this invention can be used to make a variety of products including films and fibers.

The invention has been described with reference to its preferred embodiments. Those of ordinary skill in the art may, upon reading this disclosure, appreciate changes or modifications which do not depart from the scope and spirit of the invention as described above or claimed hereafter.


-94-

## CLAIMS:

1. A compound having the general formula:



or



wherein M is Zr, Hf or Ti in its highest formal oxidation state;

$(C_5H_{4-x}R_x)$  is a cyclopentadienyl ring which is substituted with from zero to four substituent groups R, "x" is 0, 1, 2, 3 or 4 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from a group consisting of  $C_1$ - $C_{20}$  hydrocarbyl radicals, substituted  $C_1$ - $C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality,  $C_1$ - $C_{20}$  hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements; and halogen radicals, amido radicals, phosphido



-95-

radicals, alkoxy radicals, alkyl borido radicals or any other radical containing Lewis acidic or basic functionality, or  $(C_5H_{4-x}R_x)$  is a cyclopentadienyl ring in which two adjacent R-groups are joined forming  $C_4-C_{20}$  ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl;

$(JR'_{z-2})$  is a heteroatom ligand in which J is an element with a coordination number of three from Group V A or an element with a coordination number of two from Group VI A of the Periodic Table of Elements, and each  $R'$  is, independently a radical selected from a group consisting of  $C_1-C_{20}$  hydrocarbyl radicals, substituted  $C_1-C_{20}$  hydrocarbyl radicals where one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality, and "z" is the coordination number of the element J;

each Q is, independently, any univalent anionic ligand, such as a halide, hydride, or a substituted or unsubstituted  $C_1-C_{20}$  hydrocarbyl, alkoxide, aryloxy, amide, arylamide, phosphide or arylphosphide, provided that where any Q is a hydrocarbyl such Q is different from  $(C_5H_{4-x}R_x)$  or both Q together are an alkylidene, or a cyclometallated hydrocarbyl or any divalent anionic chelating ligand;

T is a covalent bridging group containing a Group IV A or V A element; and

L is a neutral Lewis base where "w" denotes a number from 0 to 3.

2. The compound of claim 1 wherein the heteroatom ligand group J element is nitrogen, phosphorous, oxygen or sulfur.

3. The compound of claim 1 wherein Q is a halide or hydrocarbyl radical.


-96-

4. The compound of claim 2 wherein the heteroatom ligand group J element is nitrogen.


5. The compound of claim 1 wherein M is hafnium, zirconium or titanium.

6. A catalyst system comprising:

(A) a Group IV B transition metal component of the formula:



or



wherein M is Ti in its highest formal oxidation state:

$(C_5H_{5-y-x}R_x)$  is a cyclopentadienyl ring which is substituted with from zero to five substituent groups R, "x" is 0, 1, 2, 3, 4 or 5 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from a group consisting of  $C_1$ - $C_{20}$  hydrocarbyl radicals, substituted  $C_1$ - $C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality,  $C_1$ - $C_{20}$  hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements;

-97-

and halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkyl borido radicals or any other radical containing Lewis acidic or basic functionality, or  $(C_5H_5-y-xR_x)$  is a cyclopentadienyl ring in which two adjacent R-groups are joined forming  $C_4-C_{20}$  ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl;

$(JR'_{z-1-y})$  is a heteroatom ligand in which J is an element with a coordination number of three from Group V A or an element with a coordination number of two from Group VI A of the Periodic Table of Elements, each  $R'$  is, independently a radical selected from a group consisting of  $C_1-C_{20}$  hydrocarbyl radicals, substituted  $C_1-C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical, or any other radical containing a Lewis acidic or basic functionality, and "z" is the coordination number of the element J;

each Q is, independently, any univalent anionic ligand such as a halide, hydride, or a substituted or unsubstituted  $C_1-C_{20}$  hydrocarbyl, alkoxide, aryloxy, amide, arylamide, phosphide or arylphosphide, provided that where Q is a hydrocarbyl such Q is different than the  $(C_5H_5-y-xR_x)$  or both Q together are an alkylidene, a cyclometallated hydrocarbyl or any divalent anionic chelating ligand;

"y" is 0 or 1 when "w" is greater than 0; "y" is 1 when "w" is 0; when "y" is 1, T is a covalent bridging group containing a Group IV A or V A element;

L is a neutral Lewis base where "w" denotes a number from 0 to 3; and

(B) is an alumoxane.

7. The catalyst system of claim 6 wherein the heteroatom ligand group J element is nitrogen, phosphorous, oxygen or sulfur.

-98-


8. The catalyst system of claim 6 wherein Q is a halogen or hydrocarbyl radical.

9. The catalyst system of claim 7 wherein the heteroatom ligand group J element is nitrogen.


10. The catalyst system of claim 6 wherein M is titanium.

11. The catalyst system of claim 6 wherein the mole ratio of aluminum atom to transition metal atom is from 10:1 to about 20,000:1.

12. A process producing a compound represented by the formula:



or



wherein M is Zr, Hf or Ti in its highest formal oxidation state;

-99-

$(C_5H_{4-x}R_x)$  is a cyclopentadienyl ring which is substituted with from zero to four substituent groups R, "x" is 0, 1, 2, 3 or 4 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from a group consisting of  $C_1$ - $C_{20}$  hydrocarbyl radicals, substituted  $C_1$ - $C_{20}$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic or basic functionality,  $C_1$ - $C_{20}$  hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements, and halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkyl borido radicals or any other radicals containing Lewis acidic or basic functionality, or  $(C_5H_{4-x}R_x)$  is a cyclopentadienyl ring in which two adjacent R-groups are joined forming  $C_4$ - $C_{20}$  ring to give a saturated or unsaturated polycyclic cyclopentadienyl ligand such as indenyl, tetrahydroindenyl, fluorenyl or octahydrofluorenyl;

$(JR'_{z-2})$  is a heteroatom ligand in which J is an element with a coordination number of three from Group V A or an element with a coordination number of two from Group VI A of the Periodic Table of Elements, and each R' is, independently a radical selected from a group consisting of  $C_1$ - $C_{20}$  hydrocarbyl radicals, substituted  $C_1$  -  $C_2$  hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or any other radical containing a Lewis acidic basic functionality, and "z" is the coordination number of the element J;

each Q is, independently, any univalent anionic ligand, such as a halide, hydride, or a substituted or unsubstituted  $C_1$ - $C_{20}$  hydrocarbyl,

-100-

alkoxide, aryloxy, amide, arylamide, phosphide or arylphosphide, provided that where Q is a hydrocarbyl such Q is different than the  $(C_5H_4-xR_x)$  or both Q together are an alkylidene, a cyclometallated hydrocarbyl or any divalent anionic chelating ligand;

T is a covalent bridging group containing a Group IV A or V A element; and

L is a neutral Lewis base where "w" denotes a number from 0 to 3;

consisting of reacting of  $d^0$  Group IV B transition metal halide with a salt containing an anion of the formula  $[(C_5H_4-xR_x)-T-(JR'_{z-2})]^{-2}$  and either two cations from the Group I A of the Periodic Table of Elements or one cation from the Group II A of the Periodic Table of Elements.

13. The process of claim 12 wherein the cation is lithium.

14. The process of claim 12 wherein the Group IV B metal halide is hafnium (IV) chloride, zirconium (IV) chloride or titanium (IV) chloride or similar compounds such as titanium (IV) chloride dietherate.




US 9005208  
SA 40656

EPO FORM P0479

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

# INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 90/0526

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC IPC <sup>5</sup> : C 07 F 7/00, 7/28, C 08 F 10/00, 4/642														
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Minimum Documentation Searched <sup>7</sup></div> <div style="display: flex; justify-content: space-between;"> <div style="width: 30%; border-bottom: 1px solid black; padding: 5px;">Classification System</div> <div style="width: 70%; border-bottom: 1px solid black; padding: 5px;">Classification Symbols</div> </div> <div style="display: flex; justify-content: space-between; padding: 5px;"> <div style="width: 30%; border-right: 1px solid black; padding: 5px;">IPC<sup>5</sup></div> <div style="width: 70%; padding: 5px;">C 07 F 7/00, C 08 F 10/00, C 08 F 4/00</div> </div> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup></div>														
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT <sup>9</sup></b> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 10%; padding: 5px;">Category <sup>9</sup></th> <th style="width: 70%; padding: 5px;">Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup></th> <th style="width: 20%; padding: 5px;">Relevant to Claim No. <sup>13</sup></th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">P,X</td> <td style="padding: 5px;">Chemische Berichte, volume 123, no. 8, August 1990, (Weinheim, DE), J. Okuda: "Synthesis and complexation of linked cyclopentadienyl-amido ligands", pages 1649-1651 see the whole article <div style="text-align: center;">--</div></td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-5</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">WO, A, 87/03887 (MITSUI PETROCHEMICAL INDUSTRIES LTD) - 2 July 1987 see claims; pages 6-9 (cited in the application) <div style="text-align: center;">--</div></td> <td style="text-align: center; vertical-align: top; padding: 5px;">1,6</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">P,A</td> <td style="padding: 5px;">Organometallics, volume 9. no. 3, 1990, (Washington, DC, US), P.J. Shapiro et al.: "{(η<sup>5</sup>-C<sub>5</sub>Me<sub>4</sub>, Me<sub>2</sub>Si(η<sup>1</sup>-NCMe<sub>3</sub>))(PMe<sub>3</sub>)SCH<sub>2</sub>}" A unique example of a single-component α-Olefin polymerization catalyst", pages 869-871 see the whole article</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1,6</td> </tr> </tbody> </table>			Category <sup>9</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	P,X	Chemische Berichte, volume 123, no. 8, August 1990, (Weinheim, DE), J. Okuda: "Synthesis and complexation of linked cyclopentadienyl-amido ligands", pages 1649-1651 see the whole article <div style="text-align: center;">--</div>	1-5	A	WO, A, 87/03887 (MITSUI PETROCHEMICAL INDUSTRIES LTD) - 2 July 1987 see claims; pages 6-9 (cited in the application) <div style="text-align: center;">--</div>	1,6	P,A	Organometallics, volume 9. no. 3, 1990, (Washington, DC, US), P.J. Shapiro et al.: "{(η <sup>5</sup> -C <sub>5</sub> Me <sub>4</sub> , Me <sub>2</sub> Si(η <sup>1</sup> -NCMe <sub>3</sub> ))(PMe <sub>3</sub> )SCH <sub>2</sub> }" A unique example of a single-component α-Olefin polymerization catalyst", pages 869-871 see the whole article	1,6
Category <sup>9</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>												
P,X	Chemische Berichte, volume 123, no. 8, August 1990, (Weinheim, DE), J. Okuda: "Synthesis and complexation of linked cyclopentadienyl-amido ligands", pages 1649-1651 see the whole article <div style="text-align: center;">--</div>	1-5												
A	WO, A, 87/03887 (MITSUI PETROCHEMICAL INDUSTRIES LTD) - 2 July 1987 see claims; pages 6-9 (cited in the application) <div style="text-align: center;">--</div>	1,6												
P,A	Organometallics, volume 9. no. 3, 1990, (Washington, DC, US), P.J. Shapiro et al.: "{(η <sup>5</sup> -C <sub>5</sub> Me <sub>4</sub> , Me <sub>2</sub> Si(η <sup>1</sup> -NCMe <sub>3</sub> ))(PMe <sub>3</sub> )SCH <sub>2</sub> }" A unique example of a single-component α-Olefin polymerization catalyst", pages 869-871 see the whole article	1,6												
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><sup>10</sup> Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 50%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p> </div> </div>														
<b>IV. CERTIFICATION</b> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; padding: 5px;">           Date of the Actual Completion of the International Search   <div style="text-align: center;">10th January 1991</div> </td> <td style="width: 50%; padding: 5px;">           Date of Mailing of this International Search Report   <div style="text-align: center;">26.02.91</div> </td> </tr> <tr> <td style="width: 50%; padding: 5px;">           International Searching Authority   <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </td> <td style="width: 50%; padding: 5px;">           Signature of Authorized Officer   <div style="text-align: center;">               Alfred Prein           </div> </td> </tr> </table>			Date of the Actual Completion of the International Search  <div style="text-align: center;">10th January 1991</div>	Date of Mailing of this International Search Report  <div style="text-align: center;">26.02.91</div>	International Searching Authority  <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer  <div style="text-align: center;">               Alfred Prein           </div>								
Date of the Actual Completion of the International Search  <div style="text-align: center;">10th January 1991</div>	Date of Mailing of this International Search Report  <div style="text-align: center;">26.02.91</div>													
International Searching Authority  <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer  <div style="text-align: center;">               Alfred Prein           </div>													